



# Polyethylene CA9150

## Description

**CA9150** is a low-density polyethylene for extrusion coating.

**CAS-No.** 9002-88-4

## Applications

**CA9150** is designed for:

Coating and lamination of aluminium foil  
Coating of various plastic films and cellophane

Extrusion coating of high volume production of boards and papers

## Additives

**CA9150** contains no additives.

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	915 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (190 °C/2,16 kg)	15 g/10min	ISO 1133
Melting temperature (DSC)	104 °C	ISO 11357-3
Maximum Coating Speed	650 m/min	BTM 14921
Minimum Coating Weight	5 g/m <sup>2</sup>	BTM 14922
Total Neck-in	66 mm	BTM 14920

## Processing Techniques

The actual conditions will depend on the type of equipment used.

A typical temperature profile from the feed zone is 240/290/300/310/310/310°C. The recommended setting for adapter and the die is 5°C lower than the melt temperature setting.

## Storage

**CA9150** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polyethylene CA9150

## Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"  
Statement on chemicals, regulations and standards  
Statement on compliance to food contact regulations  
Statement on polymer additives and BSE