



# Polyethylene LE0315-99

Thermoplastic Semiconductive Compound

## Description

**LE0315-99** has the same melt flow properties as the peroxide containing material.

## Application:

LE0315-99 is used during start up of a triple-head line. It helps to use a non-peroxide-containing material until stable conditions are reached. The settings should be the same as for the peroxide containing compound.

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1170 kg/m3	ASTM D 792

## Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
DC Volume Resistivity (23 °C)	50 Ohm.cm	ASTM D 991
DC Volume Resistivity (90 °C)	90 Ohm.cm	ASTM D 991

## Packaging

Package: Smallbins

## Storage

**LE0315-99** has a shelf life of 12 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 15 - 25 °C.