

Description

Stamylex 4066F is an octene based linear low density polyethylene produced in a solution polymerisation process using a Ziegler-Natta catalyst.

Applications

Stamylex 4066F Demonstrated applications include:

Stiff and tough films for transparent food packaging, especially in cook-in and heat sterilisation applications Non-cling layers in stretch applications

Sheets, for example for toothpaste tube construction Thermoforming applications


Special Features

Stamylex 4066F is optimised to deliver:

An excellent combination of stiffness, heat resistance, high vicat temperature and water vapour barrier properties

Physical Properties

Property	Typical Value	Test Method	
	Data should not be used for specification work		
Density (23 °C)	937 kg/m³	ISO 1183	
Melt Flow Rate (190 °C/2,16 kg)	6,2 g/10min	ISO 1133	
Melting temperature (DSC)	124 °C	ISO 11357-3	
Vicat softening temperature (10 N)	114 °C	ISO 306	



Stamylex is a registered trademark of the Borealis group.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168





Storage

Stamylex 4066F This polymer, like most polymers, is combustible so the usual precautions concerning ignition sources should be taken in warehouses and storage rooms. Where large quantities are kept in store, it is necessary to observe the normal rules for orderly stock control and it is recommended to use the first in – first out (FIFO) principle for stock planning. The products should be stored in a dry and clean facility to prevent contamination and not be exposed to direct sunlight as this may lead to quality deterioration. These materials have a shelf life of at least 3 (three) years after date of production, provided the material remains in its original unopened packaging and are stored under the storage conditions as described in this document. "Shelf life" means that there will not be any substantial difference compared to the agreed specification. The date of batch creation can be derived from the batch code printed on the bags representing. YYMMDDHHLL (LL being two letters with no reference to the production time). Borealis Plastomers generally does not sell prime material older than 2 (two) years unannounced.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168

