



Polyethylene

Casico<sup>TM</sup> FR4820

Natural Low Smoke Zero Halogen Flame Retardant Insulation Compound for Building Energy Cables

## Description

**Casico FR4820** is a thermoplastic, low smoke zero halogen (LSZH) flame retardant, UV stabilised, natural insulation compound combining with excellent extrusion properties.

It is based on the novel technology, Casico, containing inorganic filler and a novel char-forming additive which confer flame retardancy with very limited smoke generation.

## Applications

**Casico FR4820** is designed for:

70°C rated insulation for building wires (installation cables),  
flexible cords, power cables

It can be used in areas sensitive to smoke or corrosive and toxic combustion products. Casico FR4820 is stabilised for use in contact with copper.

## Specifications

**Casico FR4820** in combination meets the applicable requirements as below when processed using extrusion practice and testing procedure:

EN 50292-2-26  
EN 50363-7 TI6

EN 50363-7 TI7

## Special features

**Casico FR4820** consists of specially selected components to offer:

Low smoke and reduced toxic or corrosive gas emissions  
Excellent processing properties  
Superb system ageing compatibility  
Low water permeability

UV stabilised and suitable for colouring  
Processability on most PVC/PE extrusion equipment  
No need for pre-drying normally

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (Compound) <sup>1</sup>	1150 kg/m <sup>3</sup>	ISO 1872-2/ISO 1183
Melt Flow Rate (190 °C/2,16 kg) <sup>1</sup>	0,9 g/10min	ISO 1133
Flexural Modulus <sup>1</sup>	215 MPa	ISO 178
Tensile Strain at Break <sup>2</sup>	550 %	IEC 60811-1-1
Tensile Strength (50 mm/min) <sup>2</sup>	13 MPa	IEC 60811-1-1
Retention of Tensile Properties After Ageing (240 h, 100 °C) <sup>2</sup>	< 20 %	IEC 60811-1-2

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168





Polyethylene

# Casico FR4820

Retention of Tensile Properties After UV Ageing <sup>2</sup>	< 20 %	
Brittleness temperature <sup>1</sup>	< -60 °C	ISO 974
Hardness, Shore D ( 15 s) <sup>1</sup>	40	ISO 868
Pressure Test at High Temperature (90 °C, 4 h) <sup>2</sup>	< 50 %	IEC 60811-3-1
Cold Bend (-40 °C) <sup>2</sup>	Pass	IEC 60811-1-4
Cold Impact (-40 °C) <sup>2</sup>	Pass	IEC 60811-1-4
Water absorption (70 °C, 14 Days) <sup>2</sup>	0,1 mg/cm <sup>2</sup>	IEC 60811-1-3

<sup>1</sup> Compound

<sup>2</sup> Cable (0.7 mm insulation over 1.5 mm<sup>2</sup> solid Cu)

## Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Volume Resistivity <sup>1</sup>	10 POhm.cm	IEC 60093
Dielectric Strength <sup>1</sup>	> 20 kV/mm	IEC 60243
Breakdown Voltage <sup>2</sup>	36 kV	ISO 6722
Breakdown Duration <sup>2</sup>	Pass	IEC 60227-2/2.3

<sup>1</sup> Compound

<sup>2</sup> Cable (0.7 mm insulation over 1.5 mm<sup>2</sup> solid Cu)

## Combustion Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Temperature index <sup>1</sup>	200 °C	ISO 4589-3
Limited Oxygen Index <sup>1</sup>	27 %	
NBS Smoke Data	Optical Smoke Density Dmax	49
(76x76x0.7 mm plaque)	Time to Dmax	
Flaming mode		6 min
NBS Smoke Data	Optical Smoke Density Dmax	
(76x76x0.7 mm plaque) Non	Time to Dmax	104
Flaming mode		
Cone Calorimeter (heat flux	Ignition time	125 s
35 kW/m <sup>2</sup> , 3 mm plaque)	Average Heat Release	
	Max Heat Release	244 kW/m <sup>2</sup>
	Heat Combustion	
	Smoke Obscuration	29 MJ/dm <sup>3</sup>
	CO	
	CO <sub>2</sub>	520 m <sup>2</sup> /dm <sup>3</sup>
Corrosivity of Combustion Fumes <sup>1</sup>	0,023 kg/dm <sup>3</sup>	ISO 5660
	1,7 kg/dm <sup>3</sup>	
	1,5 µS/cm	IEC 60754-2
	5,6	

<sup>1</sup> Compound

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



Polyethylene

# Casico FR4820

## Processing Techniques

are suitable for most equipment designed for PVC/PE extrusion.

Using the below set temperatures a stable extrusion process and a cable having a smooth glossy appearance can be achieved. On-size pressure or low draw down tube-on tolling is preferred. Whichever type of tooling is used, the die should preferable have a parallel land of length equal to the final cable diameter. Homo or Copolymer based masterbatches are suitable for colouring Casico FR4820.

Barrel 1	160 °C
Barrel 2	170 °C
Barrel 3	180 °C
Barrel 4	190 °C
Die	190 °C

## Packaging

Package:           Bulk  
                      Octabins  
                      Bags

## Storage

**Casico FR4820** normally does not need pre-drying unless the material has been stored in a moist environment for a long period. In such cases drying in dehumidified air for 4 hours at 70°C will normally reduce the moisture content to an acceptable value.

## Safety

The product is not classified as a dangerous preparation. Check and follow local codes and regulations!

Please see our Safety Data Sheet for details on various aspects of safety of the product, for more information contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



Polyethylene

# Casico FR4820

## Disclaimer

**The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.**

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

**Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.**

**It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.**

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.