



Polyethylene

LE0520-99

Thermoplastic Semiconductive Compound

Description

LE0520-99

LE0520-99 has the same melt flow properties as the peroxide containing material.

APPLICATION: LE0520-99 is used during start up of a triple-head line. It helps to use a non-peroxide-containing material until stable conditions are reached. The settings should be the same as for the peroxide containing compound.

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		

Electrical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
DC Volume Resistivity (23 °C)	50 Ohm.cm	ASTM D 991
DC Volume Resistivity (90 °C)	90 Ohm.cm	ASTM D 991

Packaging

Package: Smallbins

Storage

LE0520-99 has a shelf life of 12 months from production date if stored in unopened original packages, under dry and clean conditions at temperatures between 15 - 25 °C.