

Queo™ 0230

Octene-1 Plastomer

DATA SHEET

Description and Attributes

Queo™ 0230 is an ethylene based octene plastomer produced in a solution polymerisation process using a metallocene catalyst.

Queo 0230 is designed for applications requiring:

- Free flowing pellets
- Flexibility
- Outstanding toughness and puncture resistance
- Low temperature flex-cracking and impact resistance
- High clarity
- High filler acceptance
- Excellent polyolefin compatibility

Applications

Demonstrated applications include :

- Carpet backing
- Colour master batches
- Highly filled compounds
- Powder coating
- Extrusion coated structures

Additives

Queo 0230 contains processing stabilizers

General properties	Units	Typical values [1]	Method
Melt Flow Rate (2.16 kg/190°C)	dg/min	30	ISO 1133
Density (23°C)	kg/m ³	902	ISO 1183
Shore D hardness	--	38	ISO 868
DSC peak melting point	°C	97	ISO 11357
Vicat softening temperature (at 10 N)	°C	71	ISO 306
Brittleness temperature	°C	< -76	ASTM D746

Moulded plaque properties [2]

Tensile strength at break	MPa	11	ISO 527-2 (5A)
Elongation at break	%	875	ISO 527-2 (5A)
Flexural modulus	MPa	65	ISO 178
Notched Izod at 23°C	kJ/m ²	No break	ISO 180 (1A)
Environmental stress crack resistance	hr	< 120	ASTM D1693 (method B)

Extrusion coating performance of blend with 40 weight % LDPE [3]


Neck-in at 100 m/min	cm	6.4	Internal method
Draw down	m/min	520	Internal method

[1] Values are typical and not to be interpreted as specifications.

[2] Specifics of compression moulded test specimen.

[3] Determined on pilot extrusion coating line with air gap at 170 mm, constant output at 35 rpm and 295 °C.

Queo™ 0230



Food Law Compliance and Product Handling

Queo 0230 can - in principle - be used in food contact applications in various EU Member States and in the USA (FDA). Migration or use limitations may apply. Please contact your sales representative for more detailed information and/or actual compliance certification documents.

Specific information on material safety aspects of Queo 0230 will be provided upon request.

Standard Packaging

Queo 0230 is supplied as free flowing pellets in bulk or packaged in 25 kg bags. The 25 kg bags are assembled on a heat treated pallet to a net weight of 1'375 kg and covered with a stretch hood.