



Polypropylene BD712CF

Description

BD712CF is a heterophasic copolymer.

This grade is suitable for the manufacturing of unoriented films on cast and tubular quench film lines.

Applications

BD712CF is recommended for

Food packaging
Lamination films

Stationary films
Label film

Special features

BD712CF is optimised to deliver:

Easy processability
Excellent low temperature impact

High toughness
Good seal strength

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	7 g/10min	ISO 1133
Flexural Modulus ¹	1.100 MPa	ISO 178
Melting temperature (DSC)	164 °C	ISO 11357-3
Charpy Impact Strength, notched (23 °C)	7 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	2,5 kJ/m ²	ISO 179/1eA
Molecular weight distribution	Medium	

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168

www.ponci.com.cn





Polypropylene BD712CF

Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

Property		Typical Value	Test Method
		Data should not be used for specification work	
Instrumented puncture test	Total Penetration Energy	23 J/mm	ISO 7765-2
Haze		< 40 %	ASTM D 1003
Gloss at 60 degree (of arc)		> 3	ASTM D 2457
Tensile Strain at Break	MD	750 %	ISO 527-3
Tensile Strain at Break	TD	680 %	ISO 527-3
Tensile Strength	MD	50 MPa	ISO 527-3
Tensile Strength	TD	35 MPa	ISO 527-3
Tensile Modulus	MD	650 MPa	ISO 527-3
Tensile Modulus	TD	600 MPa	ISO 527-3

Storage

BD712CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168

www.ponci.com.cn

