



Polypropylene BC918CF

Description

BC918CF is a heterophasic copolymer.

BC918CF is a high crystalline copolymer film resin.

This grade is suitable for the manufacturing of unoriented films on cast lines, conventional blown film lines with air cooling as well as roll stack process for thermoformable films/sheets.

CAS-No. 9010-79-1

Applications

BC918CF is recommended for:

Label film
Lamination films
Food packaging

Map trays
Vegetable trays

Special features

BC918CF is optimised to deliver:

Low haze
Good gloss
Very high stiffness
Good toughness

Linear tear
High seal strength
Excellent low temperature resistance

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	3,0 g/10min	ISO 1133
Flexural Modulus (2 mm/min) ¹	1.400 MPa	ISO 178
Melting temperature (DSC)	168 °C	ISO 11357-3
Charpy Impact Strength, notched (23 °C)	35 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	1,2 kJ/m ²	ISO 179/1eA
Molecular weight distribution	Medium	

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.





Polypropylene BC918CF

Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

Property	Typical Value	Test Method
Data should not be used for specification work		
Haze	4 %	ASTM D 1003
Gloss at 20 degree (of arc)	95	ASTM D 2457
Tensile Strain at Break	MD 570 %	ISO 527-3
Tensile Strain at Break	TD 530 %	ISO 527-3
Tensile Modulus	MD 1.150 MPa	ISO 527-3
Tensile Modulus	TD 980 MPa	ISO 527-3

Storage

BC918CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

General statement on compliance to food contact regulations

Statement on polymer additives and BSE

