



Polypropylene **BorsealTM TD220BF**

Description

Borseal TD220BF is a C2/C4 terpolymer

This grade is designed for sealing layers of oriented and non oriented films

Applications

Borseal TD220BF is recommended for

Sealing layer in coextrusion
Food packaging

Lamination films

Additives

Borseal TD220BF contains antiblock but no slip agent

Special features

Borseal TD220BF is optimised to deliver:

Metallisable
Optimised balance between highmelting point for easy processing and low sealing temperature
Lowest volatiles and fumes during processing
Low content of amorphous polymer
Low taste & odour

Excellent printability
Good stability of surface tension
Excellent optical properties
High seal strength and hot tack force
Wide sealing window

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	6 g/10min	ISO 1133
Melting temperature (DSC)	132 °C	ISO 11357-3
Seal Initiation Temperature (2 N) ¹	108 °C	Borealis Method
Molecular weight distribution	Medium	

¹ Measured on 30 µm coextruded BOPP film, ABA structure, 1/28/1 µm

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene

Borseal TD220BF

Storage

Borseal TD220BF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on compliance to food contact regulations

Statement on chemicals, regulations and standards

Statement on polymer additives and BSE

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene

Borseal TD220BF

Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication, however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of Borealis' products in conjunction with other materials. The information contained herein relates exclusively to our products when not used in conjunction with any third party materials.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168