

**Polypropylene****Daplen™ EF098HP**

Polypropylene TPO Compound

**Description**

**Daplen EF098HP** is a 10% mineral filled polypropylene compound intended for injection moulding. This material has an excellent balance between impact strength and stiffness and gives a good surface quality.

**Applications**

**Daplen EF098HP** has been developed especially for the car industry to be used in automotive interior parts.

Dashboards  
Door panels and pockets  
Pillar trims

Seat claddings  
Center consoles  
Automotive interior applications

**Special Features**

High scratch resistance  
Excellent surface appearance

Low density  
High purity

**Physical Properties**

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	970 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	20 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	1.800 MPa	ISO 178
Tensile Strength (50 mm/min)	22 MPa	ISO 527-2
Charpy Impact Strength, notched (-20 °C)	4 kJ/m <sup>2</sup>	ISO 179/1eA

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

**Application Related and Other Tests**

Property	Typical Value	Test Method
Data should not be used for specification work		
Fogging (100 °C, 16 h)	< 1,5 mg	DIN 75201
Emission	< 40 µgC/g	VDA 277



**Polypropylene**

# Daplen EF098HP

## Processing Techniques

The actual conditions will depend on the type of equipment used.

**Injection moulding** This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following moulding parameters should be used as guidelines:

Feeding temperature	40 - 80 °C
Mass temperature	220 - 260 °C
Back pressure	Low to medium
Holding pressure	30 - 60 bar
Mould temperature	30 - 50 °C
Screw speed	Low to medium
Flow front speed	100 - 200 mm/s

## Storage

**Daplen EF098HP** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

## Regional Availability

Europe

For information on regional availability please contact Borealis Sales Representative.