



**Polypropylene**

# Daplen™ EF341AE

Polypropylene TPO Compound

## Description

**Daplen EF341AE** is a 30% mineral filled elastomer modified polypropylene compound intended for injection moulding.

This material has excellent balanced mechanical properties, gives a good surface quality and is easy to process.

## Applications

**Daplen EF341AE** has been developed especially for the car industry to be used in automotive exterior parts.

Fender liners  
Body panels

Tailgates

## Special Features

Suitable for applications, which require low expansion over a broad temperature scale  
Very low shrinkage and post shrinkage

Excellent surface appearance

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1140 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	15 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	3.300 MPa	ISO 178
Tensile Strength (50 mm/min)	25 MPa	ISO 527-2
Heat Deflection Temperature B (0,45 MPa)	123 °C	ISO 75-2
Coefficient of Thermal Expansion (-30 °C/80 °C)	54 µm/mK	Borealis Method
Charpy Impact Strength, notched (23 °C)	7,5 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	2,5 kJ/m <sup>2</sup>	ISO 179/1eA

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

## Application Related and Other Tests

Property	Typical Value	Test Method
Data should not be used for specification work		
Mould average Shrinkage <sup>1</sup>	0,75 %	Borealis Method

<sup>1</sup> VALUES MAY ONLY BE USED AS INDICATION, AND SHOULD NOT BE USED DIRECTLY IN MOULD DESIGN WITHOUT PRIOR VALIDATION

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



**Polypropylene**

# Daplen EF341AE

## Processing Techniques

The actual conditions will depend on the type of equipment used.

### Injection Moulding

This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following parameters should be used as guidelines:

Feeding temperature	40 - 80 °C
Mass temperature	220 - 260 °C
Back pressure	Low to medium
Holding pressure	30 - 60 MPa
Mould temperature	30 - 50 °C
Screw speed	Low to medium
Flow front speed	100 - 200 mm/s

## Storage

**Daplen EF341AE** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

## Regional Availability

Europe

North America

For information on regional availability please contact Borealis Sales Representative.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168