



# **Polypropylene** **Daplen™ EH002AEB** Polypropylene Copolymer

## Description

Daplen EH002AEB is a polypropylene copolymer intended for injection moulding.

## Applications

Daplen EH002AEB has been developed especially for the car industry to be used in automotive exterior parts.

Fender liners

Automotive exterior applications

## Special features

Good impact strength at low temperature

## Physical Properties

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (23 °C)	890 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	33 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	940 MPa	ISO 178
Flexural Strength	22 MPa	ISO 178
Tensile Modulus (1 mm/min) (23 °C)	1.050 MPa	ISO 527-2
Tensile Strain at Break (50 mm/min) (23 °C)	50 %	ISO 527-2
Tensile Stress at Yield (50 mm/min) (23 °C)	19 MPa	ISO 527-2
Heat Deflection Temperature Edgewise (0,45 MPa)	80 °C	ISO 75-2
Izod Impact Strength, notched (23 °C)	10 kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact Strength, notched (-30 °C)	3,8 kJ/m <sup>2</sup>	ISO 180/1A

## Combustion Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Flammability at thickness 1 mm	Max100 mm/min	ISO 3795

## Processing Techniques

The actual conditions will depend on the type of equipment used.

Daplen EH002AEB is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 95° - 105°C. Following parameters should be used as guidelines:

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



**Polypropylene**

# Daplen EH002AEB

Melt temperature  
Holding pressure

220 - 240 °C  
50-70% of injection  
pressure

Mould temperature  
Injection speed

20 - 60 °C  
Low to medium

## Storage

**Daplen EH002AEB** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168