

**Polypropylene****Daplen™ EH119AE**

Polypropylene TPO Compound

**Description**

**Daplen EH119AE** is a 15% mineral filled elastomer modified polypropylene compound intended for injection moulding.

This material has excellent balanced mechanical properties, gives a good surface quality and is easy to process.

**Applications**

**Daplen EH119AE** has been developed especially for the automotive industry.

Bumpers

Exterior trims

**Special Features**

Excellent paintability

**Physical Properties**

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	970 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	35 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	1.750 MPa	ISO 178
Tensile Strength (50 mm/min)	19 MPa	ISO 527-2
Coefficient of Thermal Expansion (-30 °C/80 °C)	50 µm/mK	Borealis Method
Charpy Impact Strength, notched (23 °C)	55 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Impact Strength, notched (-30 °C)	6,5 kJ/m <sup>2</sup>	ISO 179/1eA

**Processing Techniques**

The actual conditions will depend on the type of equipment used.

This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following parameters should be used as guidelines:

Feeding temperature	40 - 80 °C
Mass temperature	220 - 260 °C
Back pressure	Low to medium
Holding pressure	30 - 60 bar
Mould temperature	30 - 50 °C
Screw speed	Low to medium
Flow front speed	100 - 200 mm/s

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



**Polypropylene**

**Daplen EH119AE**

### **Storage**

**Daplen EH119AE** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

### **Safety**

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

### **Recycling**

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

### **Regional Availability**

North America

For information on regional availability please contact Borealis Sales Representative.