

**Polypropylene****Daplen™ EF150HP**

Polypropylene TPO Compound

Description

Daplen EF150HP is an elastomer modified polypropylene compound intended for injection moulding.

This material has excellent balanced mechanical properties, gives a good surface quality and is easy to process.

Applications

Daplen EF150HP has been developed especially for the automotive industry.

Body panels
Bumpers
Exterior trims

Rocker panels
Front grills

Special Features

Available with and without UV-stabilisation
Low thermal expansion

Excellent stiffness at low density
High surface aesthetics

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1010 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	22 g/10min	ISO 1133
Flexural Modulus	2.100 MPa	ISO 178
Tensile Strength (50 mm/min)	23 MPa	ISO 527-2
Heat Deflection Temperature B (0,45 MPa)	110 °C	ISO 75-2
Coefficient of Thermal Expansion (-30 °C/80 °C)	54 µm/mK	Borealis Method
Charpy Impact Strength, notched (23 °C)	29 kJ/m ²	ISO 179/1eA
Charpy Impact Strength, notched (-20 °C)	4,5 kJ/m ²	ISO 179/1eA

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Processing Techniques

The actual conditions will depend on the type of equipment used.

This product is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C.

Following moulding parameters should be used as guidelines:

Feeding temperature 40 - 80 °C

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene

Daplen EF150HP

Mass temperature
Back pressure
Holding pressure
Mould temperature
Screw speed
Flow front speed

220 - 260 °C
Low to medium
30 - 60 bar
30 - 50 °C
Low to medium
100 - 200 mm/s

Storage

Daplen EF150HP should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of recovery and disposal of the product.

Regional Availability

Europe

For information on regional availability please contact Borealis Sales Representative.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168