



Polypropylene

Daplen™ MG258AIB

Polypropylene Compound, Mineral Filled

Description

Daplen MG258AIB is a 20% mineral filled polypropylene compound intended for injection moulding.

Applications

Daplen MG258AIB has been developed especially for the car industry to be used in automotive interior parts.

Interior trims

Special features

Very good combination of impact, stiffness and surface aesthetics

Physical Properties

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (23 °C)	1050 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	22 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	3.000 MPa	ISO 178
Flexural Strength	48 MPa	ISO 178
Tensile Modulus (1 mm/min) (23 °C)	3.200 MPa	ISO 527-2
Tensile Strain at Yield (50 mm/min) (23 °C)	7 %	ISO 527-2
Tensile Stress at Yield (50 mm/min) (23 °C)	33 MPa	ISO 527-2
Heat Deflection Temperature Edgewise (0,45 MPa)	125 °C	ISO 75-2
Heat Deflection Temperature Edgewise (1,80 MPa)	70 °C	ISO 75-2
Vicat softening temperature B50, (50 N)	95 °C	ISO 306
Charpy Impact Strength, notched (23 °C)	3 kJ/m ²	ISO 179/1eA
Izod Impact Strength, notched (23 °C)	3 kJ/m ²	ISO 180/1A
Hardness, Rockwell (R-scale)	102	ISO 2039-2

Combustion Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Flammability at thickness 1 mm	Max100 mm/min	ISO 3795

Processing Techniques

The actual conditions will depend on the type of equipment used.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene

Daplen MG258AIB

Daplen MG258AIB is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 95° - 105°C. Following parameters should be used as guidelines:

Melt temperature	200 - 240 °C
Holding pressure	50-70% of injection pressure
Mould temperature	20 - 40 °C
Injection speed	Low to medium

Storage

Daplen MG258AIB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168