

**Polypropylene****Fibremod™ GD250SFB**

Polypropylene Compound, Glass Fibre Reinforced

Description

Fibremod GD250SFB is a 26 % chemically coupled high performance glass fibre reinforced polypropylene compound intended for injection moulding.

This material shows excellent mechanical properties also at elevated temperatures.

Applications

Fibremod GD250SFB has been developed especially for the automotive industry.

Structural parts
White goods

Window frames

Physical Properties

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	1085 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	5 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	5.600 MPa	ISO 178
Flexural Strength	125 MPa	ISO 178
Tensile Stress at Yield (50 mm/min)	97 MPa	ISO 527-2
Heat Deflection Temperature (1,80 MPa)	150 °C	ISO 75-2
Izod Impact Strength, notched (23 °C)	12 kJ/m ²	ISO 180/1A
Izod Impact Strength, notched (-30 °C)	11 kJ/m ²	ISO 180/1A
Izod Impact Strength, unnotched (23 °C)	45 kJ/m ²	ISO 180/1U

Application Related Tests

Property	Typical Value	Test Method
Data should not be used for specification work		
Flammability at thickness 1 mm	Max100 mm/min	ISO 3795

Processing Techniques

The actual conditions will depend on the type of equipment used.

To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 95° - 105°C. Fibremod GD250SFB is easy to process with standard injection moulding machines. Following moulding parameters should be used as guidelines:

Melt temperature 200 - 240 °C



Polypropylene

Fibremod GD250SFB

Holding pressure

50-70% of injection
pressure

Mould temperature

20 - 40 °C

Injection speed

Low to medium

Storage

Fibremod GD250SFB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

Fibremod GD250SFB is not classified as a dangerous preparation. Dust and fines from the product may give a risk for dust explosion. All equipment should be properly earthed. Inhalation of dust may irritate the respiratory system and should be avoided. During processing of the product small amounts of fumes are generated, which require proper ventilation.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.