



# Polypropylene HD621CF

## Description

**HD621CF** is a homopolymer film resin, suitable for the manufacturing of unoriented film on chill roll process.

## Applications

**HD621CF** is recommended for

Food packaging  
Lamination films  
Flower packaging

Textile packaging film  
Stationary films

## Additives

**HD621CF** contains antiblock and slip agents

Additives	Content	
Antiblock (SiO <sub>2</sub> )	1500 ppm	Borealis Method
Slip (EAA)	1000 ppm	Borealis Method
Slip (OAA)	1000 ppm	Borealis Method

## Special features

**HD621CF** is optimised to deliver:

Easy processability  
Good mechanical properties  
High stiffness

Heat sterilisable  
Good optical properties

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	8 g/10min	ISO 1133
Flexural Modulus <sup>1</sup>	1.400 MPa	ISO 178
Melting temperature (DSC)	162 °C	ISO 11357-3
Molecular weight distribution	Medium	

<sup>1</sup> Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polypropylene HD621CF

## Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

Property		Typical Value	Test Method
		Data should not be used for specification work	
Instrumented puncture test	Total Penetration Energy	10 J/mm	ISO 7765-2
Haze		< 4 %	ASTM D 1003
Gloss at 20 degree (of arc)		> 105	ASTM D 2457
Tensile Strain at Break	MD	600 %	ISO 527-3
Tensile Strain at Break	TD	650 %	ISO 527-3
Tensile Strength	MD	45 MPa	ISO 527-3
Tensile Strength	TD	40 MPa	ISO 527-3
Tensile Modulus	MD	800 MPa	ISO 527-3
Tensile Modulus	TD	800 MPa	ISO 527-3
Coefficient of friction (Film/Film)		0,25	ISO 8295

## Storage

**HD621CF** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

## Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"  
Statement on chemicals, regulations and standards  
Statement on compliance to food contact regulations  
Statement on polymer additives and BSE

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168