



Description

HD601CF is a homopolymer film resin, suitable for the manufacturing of unoriented film on chill roll process.

Applications

HD601CF is recommended for

Textile packaging film Food packaging Lamination films Stationary films Flower packaging

Special features

HD601CF is optimised to deliver:

Easy processability Good mechanical properties Heat sterilisable High stiffness Good optical properties

Physical Properties

| Property | Typical Value Data should not be used fo | Test Method | |
|---|--|------------------------------------|--|
| Melt Flow Rate (230 °C/2,16 kg) Flexural Modulus ¹ Melting temperature (DSC) Molecular weight | 8 g/10min 1.400 MPa 162 °C Medium | ISO 1133 ISO 178 ISO 11357-3 | |

¹ Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.







Film Properties

Specific film values evaluated on chill roll films, produced with Borealis internal standard conditions with a thickness of 50 µm. When compared to films which were produced under other conditions. It should be taken into account that the film properties are strongly dependent on the processing conditions.

| Property | | Typical Value Test Method Data should not be used for specification work | | |
|-------------------------------------|--------------------------|--|-------------|--|
| Instrumented puncture test | Total Penetration Energy | 10 J/mm | ISO 7765-2 | |
| Haze | rotair chetration Energy | < 4 % | ASTM D 1003 | |
| Gloss at 20 degree (of arc) | | > 110 | ASTM D 2457 | |
| Tensile Strain at Break | MD | 600 % | ISO 527-3 | |
| Tensile Strain at Break | TD | 650 % | ISO 527-3 | |
| Tensile Strength | MD | 45 MPa | ISO 527-3 | |
| Tensile Strength | TD | 40 MPa | ISO 527-3 | |
| Tensile Modulus | MD | 800 MPa | ISO 527-3 | |
| Tensile Modulus | TD | 800 MPa | ISO 527-3 | |
| Coefficient of friction (Film/Film) |) | > 0.7 | ISO 8295 | |

Storage

HD601CF should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet" Statement on chemicals, regulations and standards Statement on compliance to food contact regulations Statement on polymer additives and BSE

HongRong Engineering Plastics Co.,Ltd. Head Office Tel. +85-2-6957-5415 Research Center Tel.+188 1699 6168

