



Polypropylene HG265FB

Description

HG265FB is a polypropylene homopolymer intended for fibre applications

Applications

HG265FB is recommended for

Bulked continuous filaments
Staple fibre for nonwoven

Staple fibre for textiles
Continuous filaments

Special features

HG265FB is optimised to deliver:

High flow behaviour
Medium molecular weight
Easy processability
Improved melt stability
Excellent spinning performance on low and high speed technologies

Optimal product consistency
Optimal resin purity
prolonged long term heat stability
inherent initial UV stability

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	26 g/10min	ISO 1133
Melting temperature (DSC)	161 °C	ISO 11357-3
Molecular weight distribution	Medium	

Storage

HG265FB should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet".

Safety

The product is not classified as dangerous.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene HG265FB

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

Statement on compliance to food contact regulations

Statement on polymer additives and BSE

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168