



Polypropylene Compound, Mineral Filled

Description

RB355 is a 20% mineral filled polypropylene compound intended for injection moulding.

The product is supplied in pellet form

Applications

RB355 has been developed especially for the car industry to be used in automotive interior parts.

Interior trims

Special Features

Very good balance in stiffness and impact resistance

Physical Properties

Property	Typical Value Test Method Data should not be used for specification work		
Density	1050 kg/m³	ISO 1183	
Melt Flow Rate (230 °C/2,16 kg)	20 g/10min	ISO 1133	
Flexural Modulus (2 mm/min)	2.000 MPa	ISO 178	
Tensile Stress at Yield (50 mm/min)	23 MPa	ISO 527-2	
Heat Deflection Temperature (0,45 MPa)	104 °C	ISO 75-2	
Charpy Impact Strength, notched (23 °C)	8 kJ/m²	ISO 179/1eA	
Charpy Impact Strength, notched (-20 °C)	3 kJ/m²	ISO 179/1eA	

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Application Related Tests

Property	Typical Value Test Method Data should not be used for specification work	
Flammability at thickness 1 mm	Pass100 mm/min ISO 3795	

Processing Techniques

This product is easy to process with standard injection moulding machines.

To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 95° - 105° C. Following parameters should be used as guidelines:







Melt temperature Holding pressure

Mould temperature Injection speed 200 - 240 °C 50-70% of injection pressure 20 - 40 °C Low to medium

Storage

RB355 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

RB355 is not classified as a dangerous preparation. Dust and fines from the product may give a risk for dust explosion. All equipment should be properly earthed. Inhalation of dust may irritate the respiratory system and should be avoided. During processing of the product small amounts of fumes are generated, which require proper ventilation.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.







Disclaimer

The product(s) mentioned herein are not intended to be used for medical, pharmaceutical or healthcare applications and we do not support their use for such applications.

To the best of our knowledge, the information contained herein is accurate and reliable as of the date of publication; however we do not assume any liability whatsoever for the accuracy and completeness of such information.

Borealis makes no warranties which extend beyond the description contained herein. Nothing herein shall constitute any warranty of merchantability or fitness for a particular purpose.

It is the customer's responsibility to inspect and test our products in order to satisfy itself as to the suitability of the products for the customer's particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling of our products.

No liability can be accepted in respect of the use of any Borealis product in conjunction with any other products and/or materials. The information contained herein relates exclusively to our products when not used in conjunction with any other material unless as specifically provided for in the test methods stated above.

