



Polypropylene **WG320C**

Description

WG320C is a polypropylene for extrusion coating.

CAS-No. 9002-88-4
9003-07-0

Applications

WG320C is designed for:

Micro wave oven applications
Pinholes free coating
Extrusion coating of high volume production of boards and papers

Coating of textile fibres
Coating of various plastic films and cellophane
Paper lamination films
Coating and lamination of aluminium foil

Special Features

WG320C is optimised to deliver:

Excellent processing properties
High grease resistance

High temperature resistance

Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Density	910 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	18 g/10min	ISO 1133
Melting temperature	160 °C	ISO 11357-3
Vicat softening temperature A50, (10 N)	147 °C	ISO 306
Maximum Coating Speed	450 m/min	BTM 14921
Minimum Coating Weight	12 g/m ²	BTM 14922
Total Neck-in	137 mm	BTM 14920

Storage

WG320C should be stored in dry conditions at temperatures below 50°C and protected from UV-light.

Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.



Polypropylene **WG320C**

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"

Statement on chemicals, regulations and standards

Statement on compliance to food contact regulations