



# Polypropylene WE150CF

## Description

**WE150CF** is a polyolefin resin suitable for the manufacturing of non-oriented sterilisable peelable cast films on chill roll processes.

**CAS-No.** 9010-79-1  
25087-34-7

## Applications

**WE150CF** has been evaluated according to different regulations and norms. Typical applications are mentioned below for Medical devices or Pharmaceutical & Diagnostic packaging. However, Borealis should be consulted for final approval to evaluate the use of WE150CF.

Retort food packaging  
Lamination films  
Lidding film

Medical devices class I  
Medical device packaging

For any other potential Healthcare application or end use please contact up-front your Borealis Sales Manager or Application Development Engineer.

## Additives

**WE150CF** contains antiblock and slip agents

Additives	Content	
Antiblock (SiO <sub>2</sub> )	1000 ppm	Borealis Method
Slip (EAA)	1100 ppm	Borealis Method
Calcium stearate	Yes	Borealis Method

## Special features

Seal- and peelable against itself  
Seal- and peelable against Polypropylene

Water steam sterilisable

## Physical Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Melt Flow Rate (230 °C/2,16 kg)	12,5 g/10min	ISO 1133
Flexural Modulus <sup>1</sup>	1.000 MPa	ISO 178
Melting temperature (DSC)	135 - 155 °C	ISO 11357-3

<sup>1</sup> Measured on injection moulded specimens, conditioned at 23 °C and 50 % relative humidity.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polypropylene WE150CF

## Storage

**WE150CF** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

More information on storage is found in our "Safety data sheet" / "Product safety information sheet" for this product.

## Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

## Related Documents

The following related documents are available on request, and represent various aspects on the usability, safety, recovery and disposal of the product.

"Safety data sheet" / "Product safety information sheet"  
Statement on chemicals, regulations and standards  
Statement on compliance to food contact regulations  
Statement on compliance to regulations on medical use