



Polypropylene

SR576

Polypropylene Compound

Description

SR576 is a polypropylene compound intended for injection moulding.

Applications

SR576 has been developed especially for the car industry to be used in automotive exterior parts.

Bumpers

Special features

Good stiffness and impact balance
UV resistance

Physical Properties

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (23 °C)	905 kg/m ³	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	12 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	830 MPa	ISO 178
Flexural Strength	22 MPa	ISO 178
Heat Deflection Temperature Edgewise (1,8 MPa)	50 °C	ISO 75-2
Izod Impact Strength, notched (23 °C)	45 kJ/m ²	ISO 180/1A

Combustion Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Flammability at thickness 1 mm	Max100 mm/min	ISO 3795

Processing Techniques

The actual conditions will depend on the type of equipment used.

SR576 is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following moulding parameters should be used as guidelines:

Feeding temperature	40 - 80 °C
Mass temperature	40 - 80 °C
Back pressure	Low to medium

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168



Polypropylene SR576

Holding pressure	30 - 60 MPa
Mould temperature	30 - 50 °C
Screw speed	Low to medium
Flow front speed	100 - 200 mm/s

Storage

SR576 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168