



**Polypropylene**

**SB376**

Polypropylene Compound, Mineral Filled

## Description

**SB376** is a polypropylene compound intended for injection moulding.

## Applications

**SB376** has been developed especially for the car industry to be used in automotive exterior parts.

Automotive exterior applications

## Special features

Good stiffness and impact balance

UV stabilised

## Physical Properties

Values determined on standard injection moulded specimens conditioned at 23°C and 50% relative humidity after at least 96 hours storage time.

Property	Typical Value	Test Method
Data should not be used for specification work		
Density (23 °C)	1130 kg/m <sup>3</sup>	ISO 1183
Melt Flow Rate (230 °C/2,16 kg)	10 g/10min	ISO 1133
Flexural Modulus (2 mm/min)	3.200 MPa	ISO 178
Flexural Strength	40 MPa	ISO 178
Tensile Modulus (1 mm/min) (23 °C)	3.300 MPa	ISO 527-2
Tensile Stress at Yield (50 mm/min) (23 °C)	27 MPa	ISO 527-2
Heat Deflection Temperature Edgewise (1,8 MPa)	70 °C	ISO 75-2
Izod Impact Strength, notched (23 °C)	7 kJ/m <sup>2</sup>	ISO 180/1A
Izod Impact Strength, notched (-30 °C)	2,8 kJ/m <sup>2</sup>	ISO 180/1A

## Combustion Properties

Property	Typical Value	Test Method
Data should not be used for specification work		
Flammability at thickness 1 mm	Max100 mm/min	ISO 3795

## Processing Techniques

The actual conditions will depend on the type of equipment used.

SB376 is easy to process with standard injection moulding machines. To avoid residual humidity from transport or storage, the material should be pre-dried approximately 2h at 80°C. Following moulding parameters should be used as guidelines:

Feeding temperature 40 - 80 °C

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168



# Polypropylene SB376

Mass temperature	220 - 280 °C
Back pressure	Low to medium
Holding pressure	30 - 60 MPa
Mould temperature	30 - 50 °C
Screw speed	Low to medium
Flow front speed	100 - 200 mm/s

## Storage

**SB376** should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odour generation and colour changes and can have negative effects on the physical properties of this product.

## Safety

The product is not classified as dangerous. Please see our "Safety data sheet" / "Product safety information sheet" for details on various aspects of safety, recovery and disposal of the product. For more information, contact your Borealis representative.

## Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168