



Braskem PP D130C

Braskem America Inc. - Polypropylene Homopolymer

General Information

Product Description

High bulk

Applications

Suggested uses include fine denier staple fiber, high speed fiber spinning

General

Uses	- Fibers - Staple Fibers
Agency Ratings	FDA 21 CFR 177.1520
Processing Method	Fiber (Spinning) Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	37.2	MPa	ASTM D638
Tensile Elongation ² (Yield)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant ³	1520	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	27	J/m	ASTM D256A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Additional Information	Nominal Value	Unit	Test Method
Elongation of Fibers ⁴	45	%	ASTM D2256
Suggested Takeup Roll Speed	41.7	m/sec	Internal Method
Tenacity of Fibers ⁴	3.10	g/denier	ASTM D2256

