

ATEVA® 4200ACG

Product information

Vinyl acetate content 41 %

Rheological properties

Melt Flow Index	82 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

