

VECTRA® A430

LCP/PTFE, excellent wear & electrical properties at high frequencies

Provides many of the characteristics of A130 with added lubricity. Suitable for applications requiring excellent wear characteristics. Excellent electrical properties at high frequencies. LCP/PTFE blend.

Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant FDA compliant version available UL-Listing V-0 in natural and black at 0.43mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electrical 130°C, mechanical 130°C. UL = Underwriters Laboratories (USA)

Rheological properties

Moulding shrinkage range, parallel	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	7000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	150 MPa	ISO 527-1/-2
Strain at break, 5mm/min	5.8 %	ISO 527-1/-2
Flexural Modulus	7100 MPa	ISO 178
Flexural Strength	120 MPa	ISO 178
Compressive modulus	6000 MPa	ISO 604
Compressive stress at 1% strain	38 MPa	ISO 604
Charpy impact strength, 23°C	86 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	47 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	34 kJ/m ²	ISO 180/1A
Izod impact strength, 23°C	67 kJ/m ²	ISO 180/1U
Hardness, Rockwell, M-scale	55	ISO 2039-2

Thermal properties

Melting temperature, 10°C/min	280 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	165 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	227 °C	ISO 75-1/-2
Temp. of deflection under load, 8 MPa	89 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	1 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	46 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	V-0 class	UL 94
-------------------------------	-----------	-------

Electrical properties

Relative permittivity, 100Hz	3.3	IEC 62631-2-1
Relative permittivity, 1MHz	2.7	IEC 62631-2-1
Dissipation factor, 100Hz	300 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	160 E-4	IEC 62631-2-1
Volume resistivity	1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	1E15 Ohm	IEC 62631-3-2



VECTRA® A430

Electric strength	36 kV/mm	IEC 60243-1
Comparative tracking index	PLC 3 PLC	UL 746A
Arc Resistance	130 s	Internal

Other properties

Density	1500 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	150 °C	
Drying Time, Dehumidified Dryer	4 - 6 h	
Processing Moisture Content	0.01 %	
Melt Temperature Optimum	295 °C	Internal
Screw tangential speed	0.17 - 0.18 m/s	
Max. mould temperature	80 - 120 °C	
Back pressure	3 MPa	
Injection speed	very fast	

Additional information


Injection molding	A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.
-------------------	---

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.




VECTRA® A430

Stress-strain



VECTRA® A430

Secant modulus-strain



VECTRA® A430

Processing Texts

Pre-drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -40^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V ($\leq 24\text{ h}$).

Injection molding

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.

Injection molding Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra A-grades should be dried at 150°C for a minimum of 4 hours in a desiccant dryer.

Other Approvals

Other Approvals

OEM	Specification
Continental	TST N 055 72.01-000

