

AT[®] 7110

Product information

Vinyl acetate content %

Rheological properties

Melt Flow Index	0.8 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	20 MPa	ASTM D 638
Elongation at break	600 %	ASTM D 638
Flexural Modulus	269 MPa	ASTM D 790
Shore D hardness	52	ASTM D 2240

Thermal properties

Melting temperature	114 °C	ASTM D 3418
Vicat softening temperature, 50°C/h 10N	99.6 °C	ISO 306

Other properties

Density	922 kg/m ³
---------	-----------------------

