

CELANYL® B3 HH GF35 NC 1102/HA

Polyamide 6 compound, 35% glass fibre reinforced, heat stabilized.

Designed for technical application in automotive, suitable for any application that require long term heat ageing resistance.

Product information

Part Marking Code

> PA6-GF35 <

ISO 11469

Rheological properties

Moulding shrinkage range, parallel

0.3 %

ISO 294-4, 2577

Moulding shrinkage range, normal

0.5 %

ISO 294-4, 2577

Typical mechanical properties

dry/cond.

Tensile Modulus

10800/-

MPa

ISO 527-1/-2

Stress at break, 5mm/min

185/-

MPa

ISO 527-1/-2

Strain at break, 5mm/min

3.3/-

%

ISO 527-1/-2

Charpy impact strength, 23°C

80/-

kJ/m²

ISO 179/1eU

Charpy notched impact strength, 23°C

15/-

kJ/m²

ISO 179/1eA

Izod notched impact strength, 23°C

13.5/-

kJ/m²

ISO 180/1A

Thermal properties

Melting temperature, 10°C/min

225 °C

ISO 11357-1/-3

Temp. of deflection under load, 1.8 MPa

210 °C

ISO 75-1/-2

Temp. of deflection under load, 0.45 MPa

220 °C

ISO 75-1/-2

Flammability

Burning Behav. at 1.5mm nom. thickn.

HB class

UL 94

Thickness tested

1.6 mm

UL 94

Burning Behav. at thickness h

HB class

UL 94

Thickness tested

3.2 mm

UL 94

Electrical properties

dry/cond.

Electric strength

21/-

kV/mm

IEC 60243-1

Other properties

Humidity absorption, 2mm

1.5 %

Sim. to ISO 62

Water absorption, 2mm

6 %

Sim. to ISO 62

Density

1410 kg/m³

ISO 1183

Additional information

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long

Printed: 2023-09-18



CELANYL® B3 HH GF35 NC 1102/HA

residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Processing Texts

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Injection molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

