

NILAMID B3 HH GF30 BK 9005/E - PA6

Description

PA6, 30% glass fibre reinforced, high heat aging resistant.
Car industry, Household appliances, Electrical devices.

Physical properties	dry / cond	Unit	Test Standard
Density	1360 / -	kg/m ³	ISO 1183
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
Water absorption, 23°C-sat	6.5 / *	%	ISO 62
Humidity absorption, 23°C/50%RH	1.5 / *	%	ISO 62

Mechanical properties	dry / cond	Unit	Test Standard
Tensile modulus	9500 / 5440	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	165 / 97	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	3 / 7.5	%	ISO 527-2/1A
Flexural modulus, 23°C	8600 / -	MPa	ISO 178
Flexural stress at max. force	225 / -	MPa	ISO 178
Charpy impact strength, 23°C	75 / 82.6	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	65 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	11 / -	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	8 / -	kJ/m ²	ISO 179/1eA
Izod impact notched, 23°C	11 / -	kJ/m ²	ISO 180/1A

Thermal properties	dry / cond	Unit	Test Standard
Melting point, peak	225	°C	ISO 3146
DTUL at 1.8 MPa	205 / *	°C	ISO 75-1, -2
DTUL at 0.45 MPa	220 / *	°C	ISO 75-1, -2
Flammability @3.2mm nom. thickn.	HB / *	class	UL 94
Flammability @1.6mm nom. thickn.	HB / *	class	UL 94
Flammability @0.8mm nom. thickn.	HB / *	class	UL 94
Continuous service temperature	130 / *	°C	DIN/IEC 60216-1

Electrical properties	dry / cond	Unit	Test Standard
Electric strength	21 / -	kV/mm	IEC 60243-1

Other text information

Injection Molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection moulding process should be lower than 0.15%, according to the grade and to the moulded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding

The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mould temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document "Instructions for injection moulding" or contact our technical support team.

