

Zytel® HTNFR52G45NHF NC010 (PRELIMINARY)

HIGH PERFORMANCE POLYAMIDE RESIN

Zytel® HTNFR52G45NHF NC010 is a 45% Glass Reinforced, Flame Retardant, High Performance Polyamide with improved flow. It is also a PPA resin and it uses a non-halogenated flame retardant.

Product information

Resin Identification	PA6T/66-GF45FR(40)	ISO 1043
Part Marking Code	>PA6T/66-GF45FR(40)<	ISO 11469
Part Marking Code	>PPA-GF45FR<	SAE J1344
ISO designation	ISO 16396-PA6T/66,GF45 FR(40),M1F1GN,S10-160	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.2 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.6 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile Modulus	16000 / -	MPa	ISO 527-1/-2
Stress at break, 5mm/min	170 / -	MPa	ISO 527-1/-2
Strain at break, 5mm/min	1.7 / -	%	ISO 527-1/-2
Flexural Modulus	15000 / -	MPa	ISO 178
Flexural Strength	250 / -	MPa	ISO 178
Charpy impact strength, 23°C	48 / -	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	45 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	8 / -	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	8 / -	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33 / -		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	310 / *	°C	ISO 11357-1/-3
Melting temperature, first heat	310 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	90 / 45	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	280 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel, -40-23°C	13 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	15 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel, 55-160°C	14 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	43 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	50 / *	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, 55-160°C	80 / *	E-6/K	ISO 11359-1/-2
RTI, electrical, 0.4mm	140	°C	UL 746B
RTI, electrical, 0.75mm	140	°C	UL 746B
RTI, electrical, 1.5mm	140	°C	UL 746B
RTI, electrical, 3mm	140	°C	UL 746B
RTI, strength, 0.75mm	125	°C	UL 746B



Zytel® HTNFR52G45NHF NC010 (PRELIMINARY)

HIGH PERFORMANCE POLYAMIDE RESIN

RTI, strength, 1.5mm	125 / *	°C	UL 746B
RTI, strength, 3mm	130	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at thickness h	V-0 / *	class	UL 94
Thickness tested	0.4 / *	mm	UL 94
UL recognition	yes / *		UL 94
Glow Wire Flammability Index, 0.4mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.75mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	750 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 0.4mm	700 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.5mm	750 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	800 / -	°C	IEC 60695-2-13

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	4.7 / -		IEC 62631-2-1
Relative permittivity, 1MHz	4.4 / -		IEC 62631-2-1
Dissipation factor, 100Hz	60 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	115 / -	E-4	IEC 62631-2-1
Volume resistivity	>1E13 / -	Ohm.m	IEC 62631-3-1
Electric strength	40 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112

Other properties

	dry/cond.		
Density	1600 / -	kg/m³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	6 - 8 h
Processing Moisture Content	≤0.1 %
Min. melt temperature	320 °C
Max. melt temperature	325 °C
Min. mould temperature	90 °C
Max. mould temperature	130 °C

Characteristics

Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
-----------	---



Zytel® HTNFR52G45NHF NC010 (PRELIMINARY)

HIGH PERFORMANCE POLYAMIDE RESIN

Additional information

Injection molding

For molding machine components, use corrosion resistant and wear resistant steel. For details please contact our representative. Limit the residence time of the resin in the machine. Use proper protective equipment and adequate ventilation.

