

**CELANYL® A3 D05 K15 BK 9004/E/UV - PA66**
**Description**

(NILAMID A3 D05 K15 BK 9004/E/UV)  
 PA66 15% mineral filled toughened.  
 Car industry, Household appliances, Electrical devices.

Physical properties	Value	Unit	Test Standard
Density	76.2	lb/ft <sup>3</sup>	ISO 1183
Molding shrinkage, parallel (flow)	1.2	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	1.3	%	ISO 294-4, 2577
Water absorption, 23°C-sat	6.5	%	Sim. to ISO 62
Humidity absorption, 23°C/50%RH	1.6	%	ISO 62

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	478625/-	psi	ISO 527-1, -2
Tensile stress at break, 5mm/min	11300/-	psi	ISO 527-1, -2
Tensile strain at break, 5mm/min	>20/-	%	ISO 527-1, -2
Flexural modulus, 23°C	435000/-	psi	ISO 178
Charpy notched impact strength, 23°C	2.85/-	ft-lb/in <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	2.62/-	ft-lb/in <sup>2</sup>	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
DTUL at 1.8 MPa	189	°F	ISO 75-1, -2
DTUL at 0.45 MPa	428	°F	ISO 75-1, -2
Flammability @3.2mm nom. thickn.	HB	class	UL 94
Flammability @0.8mm nom. thickn.	HB	class	UL 94

**Other text information**
**Injection Molding Preprocessing**

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection moulding process should be lower than 0.15%, according to the grade and to the moulded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

**Injection molding**

The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mould temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document 'Instructions for injection moulding' or contact our technical support team.

**Injection Molding Postprocessing**

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After moulding, in favourable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the moulded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be taken into account, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.



**CELANYL® A3 D05 K15 BK 9004/E/UV - PA66**

**Characteristics**

Special Characteristics	Auto spec approved, Heat resistant, UV resistant
Product Categories	Impact modified, Mineral reinforced
Processing	Injection molding

**Other Approvals**

OEM	Specification
Stellantis - PSA Group	FTM64 0027

