

CELANYL® A2 HH GF33 BK 9005/1A

Typical mechanical properties

Tensile Modulus	12200 MPa	ISO 527-1/-2
Stress at break, 5mm/min	185 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2.3 %	ISO 527-1/-2
Flexural Modulus	10800 MPa	ISO 178
Flexural Strength	275 MPa	ISO 178
Charpy notched impact strength, 23°C	11.5 kJ/m ²	ISO 179/1eA

Thermal properties

Temp. of deflection under load, 1.8 MPa	250 °C	ISO 75-1/-2
---	--------	-------------

Other properties

Density	1390 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	80 - 90 °C
Drying Time, Dehumidified Dryer	4 - 8 h
Processing Moisture Content	0.15 %
Max. mould temperature	60 - 80 °C

