

CELANYL® A3 GF30 NC 1102/X

Polyamide 66 compound, 30% glass fiber reinforced, UL listed HB@0.69mm
 General purpose compound for injection molding, suitable for Automotive, E&E and Industrial & Consumer applications.
 Improved flowability.

Product information

Part Marking Code > PA66-GF30 < ISO 11469

Rheological properties

Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.	
Tensile Modulus	9500/-	MPa ISO 527-1/-2
Stress at break, 5mm/min	180/-	MPa ISO 527-1/-2
Strain at break, 5mm/min	2.8/-	% ISO 527-1/-2
Flexural Modulus	8500/-	MPa ISO 178
Flexural Strength	255/-	MPa ISO 178
Charpy impact strength, 23°C	55/-	kJ/m ² ISO 179/1eU
Charpy notched impact strength, 23°C	12/-	kJ/m ² ISO 179/1eA
Izod notched impact strength, 23°C	11/-	kJ/m ² ISO 180/1A

Thermal properties

Melting temperature, 10°C/min	265 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	250 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	260 °C	ISO 75-1/-2

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94
Thickness tested	0.69 mm	UL 94
UL recognition	yes	UL 94
Glow Wire Flammability Index, 0.75mm	650 °C	IEC 60695-2-12
FMVSS Class	B	ISO 3795 (FMVSS 302)
Hot Wire Ignition, 0.75mm	PLC 4 s	UL 746A
Hot Wire Ignition, 1.5mm	PLC 1 s	UL 746A
Hot Wire Ignition, 3mm	PLC 0 s	UL 746A

Electrical properties

	dry/cond.	
Volume resistivity	>1E13/-	Ohm.m IEC 62631-3-1
Electric strength	16/-	kV/mm IEC 60243-1
Comparative tracking index	PLC 0/-	PLC UL 746A
Arc Resistance Performance Level Category	PLC 6	class UL 746B
High Amperage Arc Ignition Resistance, 0.75 mm	PLC 0	arcs UL 746A



CELANYL® A3 GF30 NC 1102/X

High Amperage Arc Ignition Resistance, 1.5 mm	PLC 0	arcs	UL 746A
High Amperage Arc Ignition Category, 1.5 mm	PLC 0	class	UL 746A
High Voltage Arc Tracking Rate	PLC 1	mm/min	UL 746A

Other properties

Humidity absorption, 2mm	1.5 %	Sim. to ISO 62
Water absorption, 2mm	5.6 %	Sim. to ISO 62
Density	1360 kg/m³	ISO 1183

Additional information

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Processing Texts

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Injection molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to



CELANYL® A3 GF30 NC 1102/X

3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

