

ECOMID® A GF33 BK 9005/1A

Typical mechanical properties

Tensile Modulus	11500 MPa	ISO 527-1/-2
Stress at break, 5mm/min	165 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2 %	ISO 527-1/-2
Flexural Modulus	11200 MPa	ISO 178
Flexural Strength	260 MPa	ISO 178
Charpy notched impact strength, 23°C	8 kJ/m ²	ISO 179/1eA

Thermal properties

Temp. of deflection under load, 1.8 MPa	230 °C	ISO 75-1/-2
---	--------	-------------

Other properties

Density	1390 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	80 - 90 °C
Drying Time, Dehumidified Dryer	4 - 8 h
Processing Moisture Content	0.15 %
Max. mould temperature	60 - 80 °C

Characteristics

Additives	Contains Recycle
-----------	------------------

