

CELSTRAN® PA66-GF30-02 AF3001 Natural

Celstran® PA66-GF30-02 is a 30% long glass fiber Polyamide. This material imparts excellent impact and modulus properties that exceed that of short fiber PA66.

Celstran® PA66-GF30-02 is a 30% long glass fiber Polyamide. This material imparts excellent impact and modulus properties that exceed that of short fiber PA66.

Typical mechanical properties

Tensile Modulus	9900 MPa	ISO 527-1/-2
Stress at break, 5mm/min	165 MPa	ISO 527-1/-2
Strain at break, 5mm/min	1.85 %	ISO 527-1/-2
Flexural Modulus	8600 MPa	ISO 178
Flexural Strength	275 MPa	ISO 178
Charpy notched impact strength, 23°C	29 kJ/m ²	ISO 179/1eA

Thermal properties

Temp. of deflection under load, 1.8 MPa	252 °C	ISO 75-1/-2
---	--------	-------------

Other properties

Density	1360 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	70 - 80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	0.18 %
Max. mould temperature	80 - 100 °C

