

## FRIANYL A3 V0XI NC 1101/Z - PA66

### Description

PA66 unfilled, flame retardant, UL classified V0@0.4mm with halogens, PBB and PBDE free, GWIT 775C (60695-2-13)  
 Car industry, Household appliances, Electrical devices.


Physical properties	dry / cond	Unit	Test Standard
Density	1340 / -	kg/m <sup>3</sup>	ISO 1183
Molding shrinkage, parallel	0.9	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577
Water absorption, 23°C-sat	5.7 / *	%	ISO 62
Humidity absorption, 23°C/50%RH	1 / *	%	ISO 62

Mechanical properties	dry / cond	Unit	Test Standard
Tensile modulus	2900 / -	MPa	ISO 527-2/1A
Tensile stress at yield, 50mm/min	55 / -	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	18.7 / -	%	ISO 527-2/1A
Charpy impact strength, 23°C	125 / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	5.7 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Izod impact notched, 23°C	6.1 / -	kJ/m <sup>2</sup>	ISO 180/1A

Thermal properties	dry / cond	Unit	Test Standard
DTUL at 1.8 MPa	90 / *	°C	ISO 75-1, -2
DTUL at 0.45 MPa	220 / *	°C	ISO 75-1, -2
Flammability @3.2mm nom. thickn.	V-0 / *	class	UL 94
Flammability @0.8mm nom. thickn.	V-0 / *	class	UL 94
UL recognition (0.4)	UL / *	-	UL 94
Continuous service temperature	110 / *	°C	DIN/IEC 60216-1

### Diagrams

#### Moldflow Specific volume-temperature (pvT)



#### Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Melt temperature	≤290	°C	-

#### Injection Molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection moulding process should be lower than 0.15%,



---

## **FRIANYL A3 V0XI NC 1101/Z - PA66**

---

according to the grade and to the moulded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically 4-8 hours at 80-90C using dehumidified air (dew point of -20C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

### **Injection molding**

---

The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290C (PA66), 235-270C (PA6), nozzle and hot runners up to 300C (up to 290C products with flame retardants). Mould temperatures: 60-80C, (80-100C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document "Instructions for injection moulding" or contact our technical support team.

### **Injection Molding Postprocessing**

---

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After moulding, in favourable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the moulded parts. Conditioning is usually carried out in hot and humid environment (for example 50C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be taken into account, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

### **Characteristics**

---

#### **Special Characteristics**

---

Flame retardant

