

# FRIANYL® A3 W GF25 V0E BK 9005

Polyamide 66 compound, 25% glass fiber reinforced, based on flame retardants halogen and red phosphorous free.  
*Designed for Electrical applications requiring self-extinguishing properties combined with good mechanical performances, this grade meets the most stringent safety requirements for insulating materials. Ideal for thicker walled parts.*

## Rheological properties

Moulding shrinkage, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.6 - 0.9 %	ISO 294-4, 2577

## Typical mechanical properties

	dry/cond.	
Tensile Modulus	9000 / -	MPa
Stress at break, 5mm/min	130 / -	MPa
Strain at break, 5mm/min	2.7 / -	%
Charpy notched impact strength, 23°C	7.5 / -	kJ/m²

## Thermal properties

Temp. of deflection under load, 1.8 MPa	210 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220 °C	ISO 75-1/-2

## Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	UL 94
Glow Wire Flammability Index, 0.75mm	960 °C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960 °C	IEC 60695-2-12
FMVSS Class	0.5	ISO 3795 (FMVSS 302)

## Electrical properties

	dry/cond.	
Volume resistivity	>1E11 / -	Ohm.m
Surface resistivity	>1E11 / -	Ohm
Electric strength	45 / -	kV/mm
Comparative tracking index	Group I	IEC 60112
Comparative tracking index	PLC 0 / -	UL 746A

## Other properties

Humidity absorption, 2mm	1.6 %	Sim. to ISO 62
Water absorption, 2mm	5.3 %	Sim. to ISO 62
Density	1360 kg/m³	ISO 1183

## Characteristics

Additives	Flame retardant
-----------	-----------------



# FRIANYL® A3 W GF25 V0E BK 9005

## Additional information


### Injection molding

The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mould temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document 'Instructions for injection moulding' or contact our technical support team.



# FRIANYL® A3 W GF25 V0E BK 9005

## Stress-strain (dry)




Printed: 2023-04-01



# FRIANYL® A3 W GF25 V0E BK 9005

## Stress-strain (cond.)




Printed: 2023-04-01



# FRIANYL® A3 W GF25 V0E BK 9005

## Secant modulus-strain (dry)




Printed: 2023-04-01



# FRIANYL® A3 W GF25 V0E BK 9005

## Secant modulus-strain (cond.)



Printed: 2023-04-01



# FRIANYL® A3 W GF25 V0E BK 9005

## Processing Texts

### Injection molding

The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mould temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document 'Instructions for injection moulding' or contact our technical support team.

### Injection molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection moulding process should be lower than 0.15%, according to the grade and to the moulded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

### Injection molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After moulding, in favourable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the moulded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be taken into account, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

## Other Approvals

### Other Approvals

OEM	Specification	Additional Information
VW Group*	VW50133	* best fitting grade to PA66-5-A, not officially approved

Printed: 2023-04-01

