

Zytel® 101F BKB009

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® 101F BKB009 is an internally lubricated polyamide 66 resin for injection moulding. It was developed for fast cycles and high productivity.

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
ISO designation	ISO 16396-PA66,,M1CG1R,S14-030	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	1.4 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.3 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile Modulus	3100 / 1400	MPa	ISO 527-1/-2
Yield stress, 50mm/min	82 / 55	MPa	ISO 527-1/-2
Yield strain, 50mm/min	4.5 / 25	%	ISO 527-1/-2
Nominal strain at break	18 / >50	%	ISO 527-1/-2
Flexural Modulus	2800 / 1200	MPa	ISO 178
Charpy notched impact strength, 23°C	5.5 / 11	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.5 / 3	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	5.5 / 11	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	5 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.37 / 0.43		

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	70 / 40	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	70 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190 / *	°C	ISO 75-1/-2
RTI, electrical, 0.75mm	130	°C	UL 746B

Printed: 2023-09-18

Page: 1 of 9



Zytel® 101F BKB009

NYLON RESIN

RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3mm	130	°C	UL 746B
RTI, electrical, 6mm	130	°C	UL 746B
RTI, impact, 0.75mm	75	°C	UL 746B
RTI, impact, 1.5mm	75	°C	UL 746B
RTI, impact, 3mm	75	°C	UL 746B
RTI, impact, 6mm	75	°C	UL 746B
RTI, strength, 0.75mm	85	°C	UL 746B
RTI, strength, 1.5mm	85/*	°C	UL 746B
RTI, strength, 3mm	85	°C	UL 746B
RTI, strength, 6mm	85	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-2/*	class	UL 94
Thickness tested	1.5/*	mm	UL 94
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-2/*	class	UL 94
Thickness tested	0.71/*	mm	UL 94
UL recognition	yes/*		UL 94
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	725/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	750/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	800/-	°C	IEC 60695-2-13
FMVSS Class	SE		ISO 3795 (FMVSS 302)

Electrical properties

	dry/cond.		
Relative permittivity, 100Hz	3.8/8		IEC 62631-2-1
Relative permittivity, 1MHz	3.6/4.6		IEC 62631-2-1
Dissipation factor, 100Hz	140/-	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	180/1000	E-4	IEC 62631-2-1
Volume resistivity	1E13/1E10	Ohm.m	IEC 62631-3-1
Electric strength	31.5/26	kV/mm	IEC 60243-1
Comparative tracking index	600/-		IEC 60112
Comparative tracking index	0/-	PLC	UL 746A

Other properties

	dry/cond.		
Humidity absorption, 2mm	2.6/*	%	Sim. to ISO 62
Water absorption, 2mm	8.5/*	%	Sim. to ISO 62
Water absorption, Immersion 24h	1.2 ^[1] /* ^[DS]	%	Sim. to ISO 62
Density	1140/-	kg/m³	ISO 1183

[DS]: Derived from similar grade

[1]: 3mm wall thickness



Zytel® 101F BKB009

NYLON RESIN

VDA Properties

Emission of organic compounds	6.5	μgC/g	VDA 277
Odour	3	class	VDA 270
Fogging, G-value (condensate)	0.1 / *	mg	ISO 6452

Injection


Drying Recommended	yes		
Drying Temperature	80 °C		
Drying Time, Dehumidified Dryer	2 - 4 h		
Processing Moisture Content	≤0.2 %		
Melt Temperature Optimum	290 °C		Internal
Min. melt temperature	280 °C		
Max. melt temperature	300 °C		
Screw tangential speed	≤0.4 m/s		
Mold Temperature Optimum	70 °C		
Min. mould temperature	50 °C		
Max. mould temperature	90 °C		
Hold pressure range	50 - 100 MPa		
Hold pressure time	4 s/mm		
Ejection temperature	190 °C		Internal



Zytel® 101F BKB009

NYLON RESIN


Stress-strain (dry)
(measured on Zytel® 101F NC010)



Zytel® 101F BKB009

NYLON RESIN


Stress-strain (cond.)
(measured on Zytel® 101F NC010)



Zytel® 101F BKB009

NYLON RESIN


Secant modulus-strain (dry)
(measured on Zytel® 101F NC010)



Zytel® 101F BKB009

NYLON RESIN

Secant modulus-strain (cond.)
(measured on Zytel® 101F NC010)



Zytel® 101F BKB009

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23 °C
- ✓ Citric Acid solution (10% by mass), 23 °C
- ✓ Lactic Acid (10% by mass), 23 °C
- ✗ Hydrochloric Acid (36% by mass), 23 °C
- ✗ Nitric Acid (40% by mass), 23 °C
- ✗ Sulfuric Acid (38% by mass), 23 °C
- ✗ Sulfuric Acid (5% by mass), 23 °C
- ✗ Chromic Acid solution (40% by mass), 23 °C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23 °C
- ✓ Sodium Hydroxide solution (1% by mass), 23 °C
- ✓ Ammonium Hydroxide solution (10% by mass), 23 °C

Alcohols

- ✓ Isopropyl alcohol, 23 °C
- ✓ Methanol, 23 °C
- ✓ Ethanol, 23 °C

Hydrocarbons

- ✓ n-Hexane, 23 °C
- ✓ Toluene, 23 °C
- ✓ iso-Octane, 23 °C

Ketones

- ✓ Acetone, 23 °C

Ethers

- ✓ Diethyl ether, 23 °C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23 °C
- ✗ SAE 10W40 multigrade motor oil, 130 °C
- ✗ SAE 80/90 hypoid-gear oil, 130 °C
- ✓ Insulating Oil, 23 °C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60 °C
- ✓ ISO 1817 Liquid 2 - M15E4, 60 °C
- ✓ ISO 1817 Liquid 3 - M3E7, 60 °C
- ✓ ISO 1817 Liquid 4 - M15, 60 °C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23 °C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23 °C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23 °C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90 °C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90 °C



Zytel® 101F BKB009

NYLON RESIN

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✗ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✗ Water, 90°C
- ✗ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

