

Zytel® EFE1068 NC010T

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® EFE1068 NC010T is a lubricated polyamide 66 for injection moulding. It has excellent flow characteristics and was developed for fast production cycles and high productivity applications.

Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
ISO designation	ISO 16396-PA66,,M1G1NR,S14-030	

Rheological properties

	dry/cond.		
Viscosity number	143 / *	cm ³ /g	ISO 307, 1157, 1628
Moulding shrinkage, parallel	1.5 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.5 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile Modulus	3000 / 1500	MPa	ISO 527-1/-2
Yield stress, 50mm/min	84 / 59	MPa	ISO 527-1/-2
Yield strain, 50mm/min	4.5 / 25	%	ISO 527-1/-2
Nominal strain at break	20 / >50	%	ISO 527-1/-2
Strain at break, 50mm/min	32 / -	%	ISO 527-1/-2
Flexural Modulus	2800 / 1300	MPa	ISO 178
Flexural Strength	120 / 75	MPa	ISO 178
Charpy impact strength, 23°C	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5 / 12	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	5 / 10	kJ/m ²	ISO 180/1A
Izod notched impact strength, -40°C	4 / -	kJ/m ²	ISO 180/1A
Hardness, Rockwell, R-scale	121 / 108		ISO 2039-2
Poisson's ratio	0.37 / 0.43		



Zytel® EFE1068 NC010T

NYLON RESIN

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	70 / 20	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	70 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	200 / *	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	260 / *	°C	ISO 306
Thermal conductivity of melt	0.14	W/(m K)	Internal
Spec. heat capacity of melt	2790	J/(kg K)	Internal
RTI, electrical, 0.75mm	130	°C	UL 746B
RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3mm	130	°C	UL 746B
RTI, electrical, 6mm	130	°C	UL 746B
RTI, impact, 0.75mm	75	°C	UL 746B
RTI, impact, 1.5mm	75	°C	UL 746B
RTI, impact, 3mm	75	°C	UL 746B
RTI, impact, 6mm	75	°C	UL 746B
RTI, strength, 0.75mm	85	°C	UL 746B
RTI, strength, 1.5mm	85 / *	°C	UL 746B
RTI, strength, 3mm	85	°C	UL 746B
RTI, strength, 6mm	85	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-2 / *	class	UL 94
Thickness tested	1.5 / *	mm	UL 94
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	V-2 / *	class	UL 94
Thickness tested	0.4 / *	mm	UL 94
UL recognition	yes / *		UL 94
Oxygen index	24 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.4mm	900 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.75mm	900 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 2mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960 / -	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 1mm	825 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 2mm	750 / -	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	775 / -	°C	IEC 60695-2-13
Glow Wire Temperature, No Flame, 1mm	750 / -	°C	IEC 60335-1
Glow Wire Temperature, No Flame, 2mm	725 / -	°C	IEC 60335-1
FMVSS Class	SE		ISO 3795 (FMVSS 302)



Zytel® EFE1068 NC010T

NYLON RESIN

Electrical properties

	dry/cond.		
Dissipation factor, 100Hz	100 / -	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	100 / -	E-4	IEC 62631-2-1
Volume resistivity	1E13 / -	Ohm.m	IEC 62631-3-1
Electric strength	27 / -	kV/mm	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112

Other properties

	dry/cond.		
Humidity absorption, 2mm	2.8 / *	%	Sim. to ISO 62
Water absorption, 2mm	8.5 / *	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183
Density of melt	950	kg/m ³	Internal

VDA Properties

Emission of organic compounds	6.5 µgC/g	VDA 277
Odour	3 class	VDA 270

Injection

Drying Recommended	yes	
Drying Temperature	80 °C	
Drying Time, Dehumidified Dryer	2 - 4 h	
Processing Moisture Content	≤0.2 %	
Melt Temperature Optimum	290 °C	Internal
Min. melt temperature	280 °C	
Max. melt temperature	300 °C	
Screw tangential speed	≤0.4 m/s	
Mold Temperature Optimum	70 °C	
Min. mould temperature	50 °C	
Max. mould temperature	90 °C	
Hold pressure range	50 - 100 MPa	
Hold pressure time	4 s/mm	
Ejection temperature	190 °C	Internal

Characteristics

Additives	Release agent
-----------	---------------

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C



Zytel® EFE1068 NC010T

NYLON RESIN

- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✗ Zinc Chloride solution (50% by mass), 23°C



Zytel® EFE1068 NC010T

NYLON RESIN

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✗ Water, 90°C
- ✗ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

