

Zytel® FR7025V0F NC010

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® FR7025V0F NC010 is an Unreinforced, Flame Retardant, Non-Halogenated Polyamide 66 for injection molding. It does not contain elemental phosphorous or heavy metals and uses an halogen free flame retardant package.

Product information

Resin Identification	PA66-FR(30)	ISO 1043
Part Marking Code	>PA66-FR(30)<	ISO 11469
ISO designation	ISO 16396-PA66,FR(30),M1F1G1NR,S14-040	

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.9 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	1.0 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.			
Tensile Modulus	3700 / 2000	MPa		ISO 527-1/-2
Yield stress, 50mm/min	* / 55	MPa		ISO 527-1/-2
Yield strain, 50mm/min	* / 20	%		ISO 527-1/-2
Stress at break, 5mm/min	80 / *	MPa		ISO 527-1/-2
Nominal strain at break	* / 30	%		ISO 527-1/-2
Strain at break, 5mm/min	10 / *	%		ISO 527-1/-2
Flexural Modulus	3700 / -	MPa		ISO 178
Charpy impact strength, 23°C	140 / -	kJ/m ²		ISO 179/1eU
Charpy notched impact strength, 23°C	3.7 / -	kJ/m ²		ISO 179/1eA
Charpy notched impact strength, -30°C	3 / -	kJ/m ²		ISO 179/1eA
Charpy notched impact strength, -40°C	3 / -	kJ/m ²		ISO 179/1eA



Zytel® FR7025V0F NC010

NYLON RESIN

Poisson's ratio 0.36/0.4

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260/*	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	80/20	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	84/*	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	240/*	°C	ISO 75-1/-2
Ball pressure test	220/-	°C	IEC 60695-10-2
Coeff. of linear therm. expansion, parallel, -40-23°C	60/*	E-6/K	ISO 11359-1/-2
CLTE, Parallel, 23-55°C(73-130°F)	65/-	E-6/K	ASTM E 831
Coeff. of linear therm. expansion, parallel, 55-160°C	70/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	70/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, Normal, 23-55°C (73-130°F)	75/-	E-6/K	ASTM E 831
Coeff. of linear therm. expansion, normal, 55-160°C	116/*	E-6/K	ISO 11359-1/-2
RTI, electrical, 0.75mm	130	°C	UL 746B
RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3mm	130	°C	UL 746B
RTI, impact, 0.75mm	75	°C	UL 746B
RTI, impact, 1.5mm	75	°C	UL 746B
RTI, impact, 3mm	75	°C	UL 746B
RTI, strength, 0.75mm	85	°C	UL 746B
RTI, strength, 1.5mm	85/*	°C	UL 746B
RTI, strength, 3mm	85	°C	UL 746B

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	UL 94
Thickness tested	1.5/*	mm	UL 94
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-0/*	class	UL 94
Thickness tested	0.75/*	mm	UL 94
UL recognition	yes/*		UL 94
Oxygen index	39/*	%	ISO 4589-1/-2
Glow Wire Flammability Index, 1.5mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 1.5mm	775/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	775/-	°C	IEC 60695-2-13
FMVSS Class	DNI ^[DS]		ISO 3795 (FMVSS 302)

[DS]: Derived from similar grade



Zytel® FR7025V0F NC010

NYLON RESIN

Electrical properties

	dry/cond.		
Electric strength	31 / 30	kV/mm	IEC 60243-1
Comparative tracking index	600 / -		IEC 60112

Other properties

	dry/cond.		
Humidity absorption, 2mm	2.5 / *	%	Sim. to ISO 62
Water absorption, Immersion 24h	1.8 ^[1] / *	%	Sim. to ISO 62
Density	1160 / -	kg/m ³	ISO 1183
[1]: wall thickness 2mm			

Injection

Drying Recommended	yes		
Drying Temperature	80 °C		
Drying Time, Dehumidified Dryer	2 - 4 h		
Processing Moisture Content	≤0.2 %		
Melt Temperature Optimum	280 °C		Internal
Min. melt temperature	270 °C		
Max. melt temperature	290 °C		
Screw tangential speed	≤0.2 m/s		
Mold Temperature Optimum	70 °C		
Min. mould temperature	50 °C		
Max. mould temperature	90 °C		
Hold pressure range	50 - 100 MPa		
Hold pressure time	3 s/mm		
Ejection temperature	210 °C		Internal

Characteristics


Additives	Release agent, Flame retardant, Non-halogenated/Red phosphorous free flame retardant
-----------	--



Zytel® FR7025V0F NC010

NYLON RESIN


Stress-strain (dry)



Zytel® FR7025V0F NC010

NYLON RESIN


Stress-strain (cond.)



Zytel® FR7025V0F NC010

NYLON RESIN


Secant modulus-strain (dry)



Zytel® FR7025V0F NC010

NYLON RESIN


Secant modulus-strain (cond.)



Zytel® FR7025V0F NC010

NYLON RESIN


Specific volume-temperature (pvT)



Zytel® FR7025V0F NC010

NYLON RESIN


Tensile modulus-temperature (dry)



Zytel® FR7025V0F NC010

NYLON RESIN

Tensile modulus-temperature (cond.)



Zytel® FR7025V0F NC010

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C



Zytel® FR7025V0F NC010

NYLON RESIN

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✗ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✗ DOT No. 4 Brake fluid, 130°C
- ✗ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✗ Water, 90°C
- ✗ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

