

Zytel® FR50 BK505

NYLON RESIN

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

Zytel® FR50 BK505 is a 25% glass fiber reinforced, flame retardant polyamide 66 resin for injection moulding.

Product information

Resin Identification	PA66-GF25FR(17)	ISO 1043
Part Marking Code	>PA66-GF25FR(17)<	ISO 11469
ISO designation	ISO 16396-PA66,GF25 FR(17),M1CF1GR,S14-110	

Rheological properties

	dry/cond.		
Viscosity number	150 ^[1] /*[DS]	cm ³ /g	ISO 307, 1157, 1628
Moulding shrinkage, parallel	0.3 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.7 / -	%	ISO 294-4, 2577
[DS]: Derived from similar grade			
[1]: Sulfuric acid 96%			

Typical mechanical properties

	dry/cond.		
Tensile Modulus	11000/8000	MPa	ISO 527-1/-2
Stress at break, 5mm/min	160/120	MPa	ISO 527-1/-2
Strain at break, 5mm/min	2.1/3	%	ISO 527-1/-2
Flexural Modulus	9500/7500	MPa	ISO 178
Charpy impact strength, 23°C	65/-	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	60/-	kJ/m ²	ISO 179/1eU
Charpy impact strength, -40°C	50/- ^[DS]	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	10/12	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	9/11	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	9/10	kJ/m ²	ISO 179/1eA
Poisson's ratio	0.34/0.34		
[DS]: Derived from similar grade			



Zytel® FR50 BK505

NYLON RESIN

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260 ^{[2]/*}	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	80/20	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	240/*	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel, -40-23°C	25/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	21/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel, 55-160°C	12/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	69/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	79/*	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, 55-160°C	110/*	E-6/K	ISO 11359-1/-2
Thermal conductivity of melt	0.25	W/(m K)	Internal
Spec. heat capacity of melt	2000	J/(kg K)	Internal
RTI, electrical, 0.75mm	130	°C	UL 746B
RTI, electrical, 1.5mm	130	°C	UL 746B
RTI, electrical, 3mm	130	°C	UL 746B
RTI, impact, 0.75mm	105	°C	UL 746B
RTI, impact, 1.5mm	115	°C	UL 746B
RTI, impact, 3mm	115	°C	UL 746B
RTI, strength, 0.75mm	105	°C	UL 746B
RTI, strength, 1.5mm	115/*	°C	UL 746B
RTI, strength, 3mm	120	°C	UL 746B

[2]: 1st heating

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	UL 94
Thickness tested	1.5/*	mm	UL 94
UL recognition	yes/*		UL 94
Burning Behav. at thickness h	V-0/*	class	UL 94
Thickness tested	0.35/*	mm	UL 94
UL recognition	yes ^{[3]/*}		UL 94
Burning Behav. 5V at thickness h	5VA/*	class	UL 94
Thickness tested	1.5/*	mm	UL 94
UL recognition	yes/*		UL 94
Oxygen index	35/*	%	ISO 4589-1/-2
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960/-	°C	IEC 60695-2-12
Glow Wire Ignition Temperature, 0.75mm	900/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 1.5mm	900/-	°C	IEC 60695-2-13
Glow Wire Ignition Temperature, 3mm	930/-	°C	IEC 60695-2-13
FMVSS Class	SE/B		ISO 3795 (FMVSS 302)

[3]: f1



Zytel® FR50 BK505

NYLON RESIN

Electrical properties

Volume resistivity	dry/cond. >1E13 / 2	Ohm.m	IEC 62631-3-1
Electric strength	.7 E10 ^[DS]		
Comparative tracking index	24 / 22 ^[DS] 275 / - ^[DS]	kV/mm	IEC 60243-1 IEC 60112

[DS]: Derived from similar grade

Other properties

Humidity absorption, 2mm	dry/cond. 1.3 / *	%	Sim. to ISO 62
Water absorption, 2mm	3.4 / * ^[DS]	%	Sim. to ISO 62
Water absorption, Immersion 24h	0.6 ^[4] / *	%	Sim. to ISO 62
Density	1600 / -	kg/m ³	ISO 1183

[DS]: Derived from similar grade

[4]: thickness, 2mm

VDA Properties

Emission of organic compounds	4.7	µgC/g	VDA 277
Odour	4.5	class	VDA 270

Injection

Drying Recommended	yes		
Drying Temperature	80	°C	
Drying Time, Dehumidified Dryer	2 - 4	h	
Processing Moisture Content	≤0.2	%	
Melt Temperature Optimum	290	°C	Internal
Min. melt temperature	280	°C	
Max. melt temperature	300	°C	
Screw tangential speed	≤0.2	m/s	
Mold Temperature Optimum	100	°C	
Min. mould temperature	70	°C	
Max. mould temperature	120	°C	
Hold pressure range	50 - 100	MPa	
Hold pressure time	3	s/mm	
Ejection temperature	210	°C	Internal

Characteristics


Additives	Flame retardant
-----------	-----------------



Zytel® FR50 BK505

NYLON RESIN


Stress-strain (dry)



Zytel® FR50 BK505

NYLON RESIN


Stress-strain (cond.)



Zytel® FR50 BK505

NYLON RESIN


Secant modulus-strain (dry)



Zytel® FR50 BK505

NYLON RESIN

Secant modulus-strain (cond.)



Zytel® FR50 BK505

NYLON RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✓ SAE 10W40 multigrade motor oil, 130°C
- ✓ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✓ ISO 1817 Liquid 1 - E5, 60°C
- ✓ ISO 1817 Liquid 2 - M15E4, 60°C
- ✓ ISO 1817 Liquid 3 - M3E7, 60°C
- ✓ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), >90°C



Zytel® FR50 BK505

NYLON RESIN

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✗ Sodium Hypochlorite solution (10% by mass), 23°C
- ✓ Sodium Carbonate solution (20% by mass), 23°C
- ✓ Sodium Carbonate solution (2% by mass), 23°C
- ✗ Zinc Chloride solution (50% by mass), 23°C

Other

- ✓ Ethyl Acetate, 23°C
- ✗ Hydrogen peroxide, 23°C
- ✓ DOT No. 4 Brake fluid, 130°C
- ✓ Ethylene Glycol (50% by mass) in water, 108°C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23°C
- ✓ 50% Oleic acid + 50% Olive Oil, 23°C
- ✓ Water, 23°C
- ✗ Water, 90°C
- ✗ Phenol solution (5% by mass), 23°C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).

