

CELSTRAN® PA66-GF50-0111P7.5/11

PA66/6 copolymer with 50% ash content - 7.5mm

Material code according to ISO 1043-1: PA66

Nylon 6.6/6 copolymer reinforced by 50 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 7.5 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

Typical mechanical properties

| | dry/cond. | | |
|---------------------------------------|---------------|-------------------|--------------|
| Tensile Modulus | 16400 / 11600 | MPa | ISO 527-1/-2 |
| Stress at break, 5mm/min | 275 / 0 | MPa | ISO 527-1/-2 |
| Stress at break, 50mm/min | 180 / 180 | MPa | ISO 527-1/-2 |
| Strain at break, 5mm/min | 2.25 / 2.5 | % | ISO 527-1/-2 |
| Flexural Modulus | 13500 / 11500 | MPa | ISO 178 |
| Flexural Strength | 380 / 300 | MPa | ISO 178 |
| Charpy impact strength, 23°C | 100 / 50 | kJ/m ² | ISO 179/1eU |
| Charpy impact strength, -30°C | 80 / - | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 40 / 36 | kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 42 / - | kJ/m ² | ISO 179/1eA |

Thermal properties

| | | |
|---|--------|----------------|
| Melting temperature, 10°C/min | 240 °C | ISO 11357-1/-3 |
| Temp. of deflection under load, 1.8 MPa | 235 °C | ISO 75-1/-2 |
| Temp. of deflection under load, 8 MPa | 220 °C | ISO 75-1/-2 |

Flammability

| | | |
|-------------------------------|----------|-------|
| Burning Behav. at thickness h | HB class | UL 94 |
| Thickness tested | 1.50 mm | UL 94 |
| UL recognition | yes | UL 94 |

Other properties

| | | |
|---------|------------------------|----------|
| Density | 1560 kg/m ³ | ISO 1183 |
|---------|------------------------|----------|

Injection

| | |
|---------------------------------|------------|
| Drying Temperature | 70 - 80 °C |
| Drying Time, Dehumidified Dryer | 2 - 4 h |
| Processing Moisture Content | 0.15 % |
| Screw tangential speed | 0.1 m/s |



CELSTRAN® PA66-GF50-0111P7.5/11

Max. mould temperature
Back pressure
Injection speed

90 - 120 °C
3 MPa
medium

