

## CELANEX® 2300B GV1/30FC - PBT

### Description

Celanex® PBT 2300B GV1/30FC is a 30% glass fiber reinforced polybutylene terephthalate with a good balance of mechanical properties and processability for use in food contact applications. Celanex® PBT 2300B GV1/30FC is suitable for injection molding applications, it is BPA-free and also free from additives derived from BPA.

Chemical abbreviation according to ISO 1043-1: PBT GF30, Polybutylene terephthalate, 30% glass fiber reinforced.

Moulding Compound ISO 7792-1: PBT, MGMN, 09-100, GF30.

Physical properties	Value	Unit	Test Standard
Density	96.8	lb/ft <sup>3</sup>	ISO 1183
Melt volume rate, MVR	12.5	cm <sup>3</sup> /10min	ISO 1133
MVR temperature	482	°F	ISO 1133
MVR load	4.76	lb	ISO 1133
Molding shrinkage, parallel (flow)	0.2 - 0.4	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	0.8 - 1.2	%	ISO 294-4, 2577
Water absorption, 23°C-sat	0.4	%	Sim. to ISO 62
Humidity absorption, 23°C/50%RH	0.2	%	ISO 62

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	1.49E6	psi	ISO 527-1, -2
Tensile stress at break, 5mm/min	21800	psi	ISO 527-1, -2
Tensile strain at break, 5mm/min	2.4	%	ISO 527-1, -2
Flexural strength, 23°C	30500	psi	ISO 178
Charpy impact strength, 23°C	26.2	ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	23.8	ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	4.52	ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	4.28	ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	437	°F	ISO 11357-1/-3
DTUL at 1.8 MPa	410	°F	ISO 75-1, -2
DTUL at 0.45 MPa	428	°F	ISO 75-1, -2
Vicat softening temperature, 50°C/h 50N	428	°F	ISO 306
Coeff. of linear therm expansion, parallel	0.139	E-4/°F	ISO 11359-2

Electrical properties	Value	Unit	Test Standard
Volume resistivity, 23°C	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity, 23°C	>1E15	Ohm	IEC 62631-3-2
Electric strength, 23°C (AC)	762	kV/in	IEC 60243-1

Rheological calculation properties	Value	Unit	Test Standard
Density of melt	82.4	lb/ft <sup>3</sup>	Internal
Thermal conductivity of melt	0.166	W/(m K)	Internal
Spec. heat capacity melt	1720	J/(kg K)	Internal
Ejection temperature	428	°F	Internal

### Typical injection moulding processing conditions

Pre Drying	Value	Unit
Necessary low maximum residual moisture content	0.02	%
Drying time	2 - 4	h
Drying temperature	248 - 284	°F



## CELANEX® 2300B GV1/30FC - PBT

Temperature	Value	Unit
Hopper temperature	68 - 122	°F
Feeding zone temperature	374 - 392	°F
Zone1 temperature	482 - 500	°F
Zone2 temperature	482 - 500	°F
Zone3 temperature	491 - 509	°F
Zone4 temperature	491 - 509	°F
Nozzle temperature	500 - 518	°F
Melt temperature	500 - 518	°F
Mold temperature	167 - 212	°F
Hot runner temperature	500 - 518	°F

Speed	Value
Injection speed	fast

Screw Speed	Value	Unit
Screw speed diameter, 25mm	90	RPM
Screw speed diameter, 40mm	75	RPM
Screw speed diameter, 55mm	60	RPM

### Other text information

#### Pre-drying

CELANEX should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be  $\leq -30^{\circ}\text{C}$ . The time between drying and processing should be as short as possible.

#### Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed ( $\leq 60\text{ h}$ ) it is necessary to lower the temperature to  $\leq 100^{\circ}\text{C}$ .

#### Injection molding

Melt Temperature 260-270 °C  
Mold Temperature \*) 75-85 °C  
Maximum Barrel Residence Time \*\*) 5-10 min  
Injection Speed fast  
Peripheral screw speed max. 0,3 m/sec  
Back Pressure 10-30 bar  
Injection Pressure 600-1000 bar  
Holding Pressure 400-800 bar  
Nozzle Design open design preferred

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided. Up to 25% clean and dry regrind may be used.

Celanese recommends only externally heated hot runner systems.

\*) For moulded parts with especially high requirements to the surface quality or dimensional stability, a mold temperature of up to 110 °C can be advantageous.

\*\*) If the cylinder temperatures are higher than the recommended maximum temperatures, the max. residence time in the barrel has to be reduced.

#### Injection Molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0,02%. The drying should be done in a dry-air dryer (dew point  $< -30^{\circ}\text{C}$ ) with a temperature of 120 to 140 °C and a drying time of 4 to min. 2 hours. In case of longer residence times in the dry-air dryer, the temperature should be reduced to 100 °C.

The time between drying and processing should be kept as short as possible. The processing machine feed hopper should be closed during the processing operation.



**CELANEX® 2300B GV1/30FC - PBT**

Product Categories	Glass reinforced
Processing	Injection molding
Regulatory	FDA food contact compliant
Delivery Form	Pellets

