

CELANEX® 3226 - PBT

Description

Celanex 3226 is a non-exuding, 20% glass-filled, flame retarded polybutylene terephthalate (PBT) which has an excellent balance of mechanical properties and processability. It is well suited for electrical connectors and maintains its UL ratings with up to 50% regrind.

Physical properties	Value	Unit	Test Standard
Density	1600	kg/m ³	ISO 1183
Melt volume rate, MVR	9	cm ³ /10min	ISO 1133
MVR temperature	250	°C	ISO 1133
MVR load	2.16	kg	ISO 1133
Molding shrinkage, parallel	0.2 - 0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5 - 0.8	%	ISO 294-4, 2577
Water absorption, 23°C-sat	0.4	%	ISO 62
Humidity absorption, 23°C/50%RH	0.15	%	ISO 62

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	7200	MPa	ISO 527-2/1A
Tensile stress at break, 5mm/min	115	MPa	ISO 527-2/1A
Tensile strain at break, 5mm/min	2.5	%	ISO 527-2/1A
Flexural modulus, 23°C	7200	MPa	ISO 178
Flexural strength, 23°C	185	MPa	ISO 178
Charpy impact strength, 23°C	35	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	35	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	6.5	kJ/m ²	ISO 179/1eA
Ball indentation hardness, 30s	208	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	225	°C	ISO 11357-1/-3
DTUL at 1.8 MPa	203	°C	ISO 75-1, -2
DTUL at 0.45 MPa	220	°C	ISO 75-1, -2
DTUL at 8.0 MPa	135	°C	ISO 75-1, -2
Vicat softening temperature, 50°C/h 50N	220	°C	ISO 306
Coeff. of linear therm expansion, parallel	0.35	E-4/°C	ISO 11359-2
Coeff. of linear therm expansion, normal	0.35	E-4/°C	ISO 11359-2
Limiting oxygen index (LOI)	30	%	ISO 4589-1/-2
Flammability @1.6mm nom. thickn.	V-0	class	UL 94
thickness tested (1.6)	1.6	mm	UL 94
UL recognition (1.6)	UL	-	UL 94
Flammability at thickness h	V-0	class	UL 94
thickness tested (h)	0.38	mm	UL 94
UL recognition (h)	UL	-	UL 94

Electrical properties	Value	Unit	Test Standard
Relative permittivity, 50Hz	4.3	-	IEC 60250
Relative permittivity, 1MHz	3.9	-	IEC 60250
Dissipation factor, 50Hz	33	E-4	IEC 60250
Dissipation factor, 1MHz	160	E-4	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
Electric strength	32	kV/mm	IEC 60243-1
Comparative tracking index	225	-	IEC 60112
Arc resistance	87	s	Internal



CELANEX® 3226 - PBT

Pre Drying	Value	Unit	Test Standard
Necessary low maximum residual moisture content	0.02	%	-
Drying time	4	h	-
Drying temperature	120 - 130	°C	-
Temperature	Value	Unit	Test Standard
Hopper temperature	20 - 50	°C	-
Feeding zone temperature	230 - 240	°C	-
Zone1 temperature	230 - 240	°C	-
Zone2 temperature	235 - 250	°C	-
Zone3 temperature	235 - 250	°C	-
Zone4 temperature	240 - 260	°C	-
Nozzle temperature	250 - 260	°C	-
Melt temperature	235 - 260	°C	-
Mold temperature	65 - 93	°C	-
Hot runner temperature	250 - 260	°C	-
Speed	Value	Unit	Test Standard
Injection speed	medium-fast	-	-

Other text information

Pre-drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

Injection molding

Rear Temperature 450-470(230-240) deg F (deg C)
Center Temperature 460-480(235-250) deg F (deg C)
Front Temperature 470-500(240-260) deg F (deg C)
Nozzle Temperature 480-500(250-260) deg F (deg C)
Melt Temperature 460-500(235-260) deg F (deg C)
Mold Temperature 150-200(65-93) deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Characteristics

Special Characteristics

Flame retardant

Delivery Form

Pellets

Product Categories

Glass reinforced

Additives

Release agent, Flame retarding agent

Processing

Injection molding

