

CELANEX® 3202-2

20% glass-fiber reinforced; lubricated; high flow PBT grade

Celanex 3202-2 is a 20% glass-filled Polybutylene Terephthalate that has an excellent balance of mechanical properties and processability. It contains an internal lubricant for mold release.

Product information

| | | |
|-------------------|----------|-----------|
| Part Marking Code | PBT-GF20 | ISO 11469 |
|-------------------|----------|-----------|

Rheological properties

| | | |
|------------------------------------|-------------|-----------------|
| Melt mass-flow rate | 22 g/10min | ISO 1133 |
| Melt mass-flow rate, Temperature | 250 °C | |
| Melt mass-flow rate, Load | 2.16 kg | |
| Moulding shrinkage range, parallel | 0.4 - 0.8 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|------------------------------------|----------|--------------|
| Stress at break, 5mm/min | 115 MPa | ISO 527-1/-2 |
| Strain at break, 5mm/min | 3.2 % | ISO 527-1/-2 |
| Flexural Modulus | 6800 MPa | ISO 178 |
| Flexural Strength | 180 MPa | ISO 178 |
| Izod notched impact strength, 23°C | 7 kJ/m² | ISO 180/1A |

Thermal properties

| | | |
|-------------------------------|--------|----------------|
| Melting temperature, 10°C/min | 225 °C | ISO 11357-1/-3 |
|-------------------------------|--------|----------------|

Other properties

| | | |
|--------------------------|------------|----------------|
| Humidity absorption, 2mm | 0.1 % | Sim. to ISO 62 |
| Density | 1450 kg/m³ | ISO 1183 |

Injection

| | |
|---------------------------------|--------------|
| Drying Temperature | 120 - 130 °C |
| Drying Time, Dehumidified Dryer | 4 h |
| Processing Moisture Content | 0.02 % |
| Max. mould temperature | 65 - 93 °C |
| Injection speed | medium-fast |

Characteristics

| | |
|-----------|---------------|
| Additives | Release agent |
|-----------|---------------|

Additional information

| | |
|-------------------|---|
| Injection molding | Rear Temperature 450-470(230-240) deg F (deg C) |
| | Center Temperature 460-480(235-250) deg F (deg C) |
| | Front Temperature 470-500(240-260) deg F (deg C) |
| | Nozzle Temperature 480-500(250-260) deg F (deg C) |



CELANEX® 3202-2

Melt Temperature 460-500(235-260) deg F (deg C)
Mold Temperature 150-200(65-93) deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Processing Texts

Pre-drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

Injection molding

Rear Temperature 450-470(230-240) deg F (deg C)
Center Temperature 460-480(235-250) deg F (deg C)
Front Temperature 470-500(240-260) deg F (deg C)
Nozzle Temperature 480-500(250-260) deg F (deg C)
Melt Temperature 460-500(235-260) deg F (deg C)
Mold Temperature 150-200(65-93) deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Injection molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours.

