

CELANEX® DEV 3319 (PRELIMINARY)

30% glass-fiber reinforced, flame retardant grade, non-exuding

Celanex DEV 3319 is a non-exuding flame retarded, 30% fiberglass reinforced polybutylene terephthalate which has an excellent balance of mechanical properties and processability. It is well suited for electrical connector applications.

Rheological properties

Melt volume-flow rate	5 cm ³ /10min	ISO 1133
Temperature	250 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Modulus	11500 MPa	ISO 527-1/-2
Stress at break, 5mm/min	140 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2 %	ISO 527-1/-2
Charpy impact strength, 23°C	50 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	8.5 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
-------------------------------	--------	----------------

Flammability

Burning Behav. at thickness h	V-0 class	UL 94
Thickness tested	0.8 mm	UL 94

Other properties

Density	1650 kg/m ³	ISO 1183
---------	------------------------	----------

Characteristics

Additives	Flame retardant
-----------	-----------------

Additional information

Injection molding	Rear Temperature 450-470(230-240) deg F (deg C) Center Temperature 460-480(235-250) deg F (deg C) Front Temperature 470-490(240-255) deg F (deg C) Nozzle Temperature 480-490(250-255) deg F (deg C) Melt Temperature 460-490(235-255) deg F (deg C) Mold Temperature 150-200(65-93) deg F (deg C) Back Pressure 0-50 psi Screw Speed Medium Injection Speed Fast
-------------------	---

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of



CELANEX® DEV 3319 (PRELIMINARY)

the material has to be avoided, in particular for flame retardant grades. Up to 50% clean and dry regrind may be used for the '16 series' flame retardant grades.

Processing Texts

Pre-drying

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.

Injection molding

Rear Temperature 450-470(230-240) deg F (deg C)
Center Temperature 460-480(235-250) deg F (deg C)
Front Temperature 470-490(240-255) deg F (deg C)
Nozzle Temperature 480-490(250-255) deg F (deg C)
Melt Temperature 460-490(235-255) deg F (deg C)
Mold Temperature 150-200(65-93) deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Medium
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 50% clean and dry regrind may be used for the '16 series' flame retardant grades.

Injection molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30°F (-34°C) at 250°F (121°C) for 4 hours..

