

Rynite® FR533NH BK507 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Common features of Rynite® thermoplastic polyester include mechanical and physical properties such as excellent balance of strength and stiffness, dimensional stability, creep resistance, heat resistance, high surface gloss and good inherent electrical properties at elevated temperature. It can be processed over a broad temperature range and has excellent flow properties.

Rynite® thermoplastic polyester resins are typically used in demanding applications in the automotive, electrical and electronics, appliances where they successfully replace metals and thermosets, as well as other thermoplastic polymers.

Rynite® FR533NH BK507 is a 33% glass reinforced, modified polyethylene terephthalate resin using a non-halogenated flame retardant.

Product information

Resin Identification	PET- GF33FR(40)	ISO 1043
Part Marking Code	>PET-GF33FR(40)<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.4 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	12900 MPa	ISO 527-1/-2
Stress at break, 5mm/min	82 MPa	ISO 527-1/-2
Strain at break, 5mm/min	0.9 %	ISO 527-1/-2
Flexural Modulus	13100 MPa	ISO 178
Flexural Strength	137 MPa	ISO 178
Charpy notched impact strength, 23°C	9 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -40°C	9 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33	

Thermal properties

Melting temperature, 10°C/min	249 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	90 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	240 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel, -40-23°C	16 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	18 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel, 55-160°C	12 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	54 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	78 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, 55-160°C	93 E-6/K	ISO 11359-1/-2
RTI, electrical, 0.4mm	155 °C	UL 746B
RTI, electrical, 0.75mm	155 °C	UL 746B



Rynite® FR533NH BK507 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

RTI, electrical, 1.5mm	155 °C	UL 746B
RTI, electrical, 3mm	155 °C	UL 746B
RTI, impact, 0.75mm	160 °C	UL 746B
RTI, impact, 1.5mm	170 °C	UL 746B
RTI, impact, 3mm	170 °C	UL 746B
RTI, strength, 0.75mm	160 °C	UL 746B
RTI, strength, 1.5mm	170 °C	UL 746B
RTI, strength, 3mm	170 °C	UL 746B

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	UL 94
Thickness tested	1.5 mm	UL 94
UL recognition	yes	UL 94
Burning Behav. at thickness h	V-0 class	UL 94
Thickness tested	0.4 mm	UL 94
UL recognition	yes	UL 94
Burning Behav. 5V at thickness h	5VA class	UL 94
Thickness tested	0.75 mm	UL 94
UL recognition	yes	UL 94
Railway classification	R22	EN 45545-2
Railway classification rating	HL1	EN 45545-2

Electrical properties

Volume resistivity	1E13 Ohm.m	IEC 62631-3-1
Electric strength	31 kV/mm	IEC 60243-1

Other properties

Density	1600 kg/m³	ISO 1183
---------	------------	----------

Injection

Drying Recommended	yes	
Drying Temperature	120 °C	
Drying Time, Dehumidified Dryer	4 - 6 h	
Processing Moisture Content	≤0.02 ^[1] %	
Melt Temperature Optimum	280 °C	Internal
Min. melt temperature	270 °C	
Max. melt temperature	280 °C	
Min. mould temperature	120 °C	
Max. mould temperature	140 ^[2] °C	

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)



Rynite® FR533NH BK507 (PRELIMINARY)

THERMOPLASTIC POLYESTER RESIN

Characteristics

Additives

Flame retardant, Non-halogenated/Red phosphorous free flame retardant

