

General purpose, improved flow, minimize noise (squeak) when wearing against itself. Celcon® M140-L1 is a general purpose acetal copolymer material with a slightly lower viscosity for improved flow in molding that has been modified to reduce or eliminate noise (squeak) when wearing against itself.

Rheological properties

Melt volume-flow rate Temperature Load Moulding shrinkage range, parallel	12 190 2.16 1.9	cm ³ /10min °C kg %	ISO 1133 ISO 294-4, 2577
Moulding shrinkage range, normal	1.7	%	ISO 294-4, 2577
Typical mechanical properties			
Tensile Modulus	2600	MPa	ISO 527-1/-2
Yield stress, 50mm/min	63	MPa	ISO 527-1/-2
Yield strain, 50mm/min	9.5	%	ISO 527-1/-2
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress at 3.5%	71	MPa	ISO 178
Charpy notched impact strength, 23°C	6	kJ/m²	ISO 179/1eA
Izod notched impact strength, 23°C	5.7	kJ/m²	ISO 180/1A
Thermal properties			
Melting temperature, 10°C/min	166	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	161	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Other properties			
Density	1400	kg/m ³	ISO 1183
Density of melt	1160	kg/m ³	Internal
Injection			
Drving Temperature	100 - 120	°C	
Drving Time. Dehumidified Drver	3 - 4	h	
Max. mould temperature	80 - 120	°C	
Back pressure	4	MPa	
Injection speed	slow-medium		

Additional information

Injection molding

Standard reciprocating screw injection molding machines with a high compression screw (minimum 3:1 and preferably 4:1) and low back pressure (0.35 Mpa/50 PSI) are favored. Using a low compression screw (I.E. general purpose 2:1 compression ratio) can result in unmelted particles and poor melt homogeneity. Using a high back pressure to make up for a low compression ratio

Printed: 2023-09-15



Page: 1 of 7





may lead to excessive shear heating and deterioration of the material.

Melt Temperature: Preferred range 182-199 C (360-390 F). Melt temperature should never exceed 230 C (450 F).

Mold Surface Temperature: Preferred range 82-93 C (180-200 F) especially with wall thickness less than 1.5 mm (0.060 in.). May require mold temperature as high as 120 C (250 F) to reproduce mold surface or to assure minimal molded in stress. Wall thickness greater than 3mm (1/8 in.) may use a cooler (65 C/150 F) mold surface temperature and wall thickness over 6mm (1/4 in.) may use a cold mold surface down to 25 C (80 F). In general, mold surface temperatures lower than 82 C (180 F) may hinder weld line formation and produce a hazy surface or a surface with flow lines, pits and other included defects that can hinder part performance.

Printed: 2023-09-15



Page: 2 of 7





Stress-strain





Page: 3 of 7





Secant modulus-strain







Page: 4 of 7





True stress-strain



Printed: 2023-09-15



Page: 5 of 7





Processing Texts					
Pre-drying	Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.				
Injection molding	Standard reciprocating screw injection molding machines with a high compression screw (minimum 3:1 and preferably 4:1) and low back pressure (0.35 Mpa/50 PSI) are favored. Using a low compression screw (I.E. general purpose 2:1 compression ratio) can result in unmelted particles and poor melt homogeneity. Using a high back pressure to make up for a low compression ratio may lead to excessive shear heating and deterioration of the material.				
	Melt Temperature: Preferre should never exceed 230 C	<i>I</i> lelt Temperature: Preferred range 182-199 C (360-390 F). Melt temperature hould never exceed 230 C (450 F).			
	Mold Surface Temperature: Preferred range 82-93 C (180-200 F) especially with wall thickness less than 1.5 mm (0.060 in.). May require mold temperature as hig as 120 C (250 F) to reproduce mold surface or to assure minimal molded in stress. Wall thickness greater than $3mm (1/8 in.)$ may use a cooler (65 C/150 F) mold surface temperature and wall thickness over $6mm (1/4 in.)$ may use a cold mold surface down to 25 C (80 F). In general, mold surface temperatures lower than 82 C (180 F) may hinder weld line formation and produce a hazy surface or surface with flow lines, pits and other included defects that can hinder part performance.				
Injection molding Preprocessing	Drying is generally not required because Celcon® and Hostaform® acetal copolymers are not hydroscopic nor are they degraded by moisture during processing. Excessive moisture can lead to splay (silver streaking) in molded parts. For better uniformity in molding especially when using regrind or material that has been stored in containers open to the atmosphere, recommended drying conditions are 80 C (180 F) for 3hours. Desiccant hopper dryers are not required. Maximum water content = 0.35%				
Injection molding Postprocessing	Postprocessing conditioning and moisturizing are not required. It may be necessary to fixture large or complicated parts with varying wall thickness to prevent warpage while cooling to ambient temperature.				
Other Approvals					
Other Approvals	OEM	Specification	Additional Information		
	Stellantis - Chrysler	CPN 4570	Natural		
	Stellantis - Chrysler	CPN 4597	Black		

Printed: 2023-09-15



Page: 6 of 7

