

HOSTAFORM® C 9021 SW

Injection molding type like C 9021; special modified with anti-friction additives for prevention of squeaking noise

Chemical abbreviation according to ISO 1043-1: POM-KD10

Molding compound ISO 29988-POM-K,KD10,GNRS2,3-2

POM copolymer Injection molding type, special modified with anti-friction additives for prevention of squeaking noise; good chemical resistance to solvents, fuel and strong alkalis as well as good hydrolysis resistance; high resistance to thermal and oxidative degradation. UL-registration in natural and black and a thickness more than 1.5 mm as UL 94 HB. Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness more than 1,5 mm. Ranges of applications: For sliding combinations with low wear and low coefficient of friction, prevents squeaking noise. UL = Underwriters Laboratories (USA) FMVSS = Federal Motor Vehicle Safety Standard (USA)

Product information

Part Marking Code	POM-KD10	ISO 11469
-------------------	----------	-----------

Rheological properties

Melt volume-flow rate	6.5 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage range, parallel	2.1 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	2850 MPa	ISO 527-1/-2
Yield stress, 50mm/min	53 MPa	ISO 527-1/-2
Yield strain, 50mm/min	7 %	ISO 527-1/-2
Nominal strain at break	16 %	ISO 527-1/-2
Tensile creep modulus, 1h	2400 MPa	ISO 899-1
Tensile creep modulus, 1000h	1200 MPa	ISO 899-1
Charpy impact strength, 23°C	90 kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	85 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	4 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4 kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 358/30	135 MPa	ISO 2039-1

Thermal properties

Melting temperature, 10°C/min	166 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	80 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	140 °C	ISO 306
Coeff. of linear therm. expansion, parallel	120 E-6/K	ISO 11359-1/-2



HOSTAFORM® C 9021 SW

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Thickness tested	1.6 mm	UL 94
Burning Behav. at thickness h	HB class	UL 94
Thickness tested	3.18 mm	UL 94
UL recognition	yes	UL 94

Electrical properties

Relative permittivity, 100Hz	4.1	IEC 62631-2-1
Relative permittivity, 1MHz	4.1	IEC 62631-2-1
Dissipation factor, 100Hz	35 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	75 E-4	IEC 62631-2-1
Volume resistivity	1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Comparative tracking index	PLC 0 PLC	UL 746A

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	1.2 %	Sim. to ISO 62
Density	1420 kg/m³	ISO 1183

Injection

Drying Temperature	100 - 120 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	0.15 %
Screw tangential speed	0.2 - 0.21 m/s
Max. mould temperature	80 - 120 °C
Back pressure	2 MPa
Injection speed	slow

Characteristics

Additives	Release agent
-----------	---------------


Additional information

Injection molding	Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.
-------------------	--



HOSTAFORM® C 9021 SW

Stress-strain




Printed: 2023-09-15



HOSTAFORM® C 9021 SW

Secant modulus-strain




Printed: 2023-09-15



HOSTAFORM® C 9021 SW

Stress-strain (isochronous) 23°C




Printed: 2023-09-15



HOSTAFORM® C 9021 SW

Creep modulus-time 23°C



Printed: 2023-09-15



HOSTAFORM® C 9021 SW

Processing Texts

Pre-drying	Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.
Longer pre-drying times/storage	The product can then be stored in standard conditions until processed.
Injection molding	Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.
Injection molding Preprocessing	General drying is not necessary due to low moisture absorption of the resin. In case of bad storage conditions (water contact or condensed water) the use of a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended. Max. Water content 0,2 %
Injection molding Postprocessing	Conditioning e.g. moisturizing is not necessary.

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Bosch	N28 BN22-O015	Natural & Black
Continental	TST N 055 54.23	
Nissan	POM(0xx)-lxx-1	

Printed: 2023-09-15

